

## Important information

The tables “Chemical resistance of plastics”, “Plastics and their properties” and “Viscosity of liquids” as well as the information about chemical resistance given in the particular product descriptions have been drawn up based on information provided by various raw material manufacturers. These values are based solely on laboratory tests with raw materials. Plastic components produced from these raw materials are frequently subject to influences that cannot be recognized in laboratory tests (temperature, pressure, material stress, effects of chemicals, construction features, etc.). For this reason the values given are only to be regarded as being guidelines. In critical cases it is essential that a test is carried out first. No legal claims can be derived from this information; nor do we accept any liability for it. A knowledge of the chemical and mechanical resistance alone is not sufficient for the evaluation of the usability of a product. For example, the regulations concerning flammable liquids (explosion prevention) must also be taken into consideration.

「プラスチックの耐薬品性」、「プラスチックとその特性」および「液体の粘度」の表、ならびに個々の製品の説明に記載されている耐薬品性に関する情報は、さまざまな原材料メーカーから提供された情報に基づいて作成されています。これらの値は、原材料を使用した実験室でのテストのみに基づいています。これらの原材料から製造されたプラスチック部品は、実験室でのテストでは認識できない影響（温度、圧力、材料の応力、化学物質の影響、構造上の特徴など）を受けることがよくあります。このため、示されている値はガイドラインとしてのみ考慮してください。重要な場合には、最初にテストを実行することが不可欠です。この情報から法的な主張をすることはできません。また、当社はこれについて一切の責任を負いません。製品の有用性を評価するには、耐薬品性および機械的耐性の知識だけでは不十分です。たとえば、可燃性液体（爆発防止）に関する規制も考慮する必要があります。

## Copyright

This table has been published and updated by Bürkle GmbH, D-79415 Bad Bellingen as a work of reference. This Copyright clause must not be removed. The table may be freely passed on and copied, provided that the information about the publisher is retained.

この表は、Bürkle GmbH, D-79415 Bad Bellingen によって参考資料として公開および更新されています。この著作権条項は削除しないでください。発行者に関する情報が保持されている限り、表は自由に転送およびコピーできます。

## Extensions, additions and translations

If your own experiences with materials and media could be used to extend this table then we would be pleased to receive any additional information. Please send an E-Mail to [info@buerkle.de](mailto:info@buerkle.de). We would also like to receive translations into other languages. Please visit our website at [www.buerkle.de](http://www.buerkle.de) from time to time and download the updated version of these lists.

ご自身の素材やメディアに関する経験に基づいてこの表を拡張できる場合は、追加情報をお送りいただければ幸いです。[info@buerkle.de](mailto:info@buerkle.de) まで電子メールをお送りください。他の言語への翻訳もお待ちしております。定期的に当社の Web サイト [www.buerkle.de](http://www.buerkle.de) にアクセスし、これらのリストの更新バージョンをダウンロードしてください。

## Publisher

Bürkle GmbH  
Rheinauen 5  
D-79415 Bad Bellingen  
Tel +49 (76 35) 8 27 95-0  
Fax +49 (76 35) 8 27 95-31  
[info@buerkle.de](mailto:info@buerkle.de)  
[www.buerkle.de](http://www.buerkle.de)

Version 3.9 (11.01.2021)

CHEMICALS	FORMULA	CAS-NR.	CONCENTRATION	HAZARD NOTE	FLAMMABLE	thermoplastics																fluoroplastics		elastomers		metals		COMMENT																					
						HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HART	PVC WEICH	SAN	ECTFE /ETFE	FEP	PTFE	PVDF	EPDM	FPM /FKM	NBR	SI	AL		V2A	V4A	Hastelloy C																		
Acetaldehyde	C <sub>2</sub> H <sub>4</sub> O	000075-07-0	40 %	F+, Xn	X	3/3	2/4	2/0	4/4	(4)	2/4	2/0	3/4	4/4	4/4	4/4	0/0	4/4	2/3	(1)	1/1	4/4	3/0	4/4	4/4	0/0	(1)	(1)	(1)	3/4	Acetic aldehyde; Ethanal; Ethyl aldehyde																		
Acetaldehyde	C <sub>2</sub> H <sub>4</sub> O	000075-07-0	techn. pure	F+, Xn	X	3/3	2/4	2/0	4/4	(4)	2/4	2/0	3/4	4/4	4/4	4/4	0/0	4/4	2/3	(1)	1/1	4/4	3/0	4/4	4/4	0/0	(1)	(1)	(1)	1/1																			
Acetamide	C <sub>2</sub> H <sub>5</sub> NO	000060-35-5	saturated	Xn		1/1	1/1	1/0	4/4	0/0	1/1	1/0	1/1	1/1	4/4	4/4	0/0	1/1	1/1	1/1	1/1	1/1	1/0	4/4	1/0	0/0	(1)	(1)	(1)	1/1																			
Acetic acid	C <sub>2</sub> H <sub>4</sub> O <sub>2</sub>	000064-19-7	50 %	C		1/1	1/1	4/4	1/2	0/0	1/1	3/4	1/1	2/2	2/2	1/2	0/0	0/0	1/2	1/1	1/1	1/1	4/4	4/4	4/4	0/0	1/3	1/1	1/1	1/1																			
Acetic acid	C <sub>2</sub> H <sub>4</sub> O <sub>2</sub>	000064-19-7	100 %	C+	X	0/0	0/0	4/4	4/4	4/4	(3)	4/4	1/3	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	4/4	4/4	4/4	0/0	1/3	1/2	1/2	1/1																			
Acetic acid	C <sub>2</sub> H <sub>4</sub> O <sub>2</sub>	000064-19-7	90%	C+	X	1/1	1/2	4/4	4/4	4/4	1/3	4/4	1/2	4/4	3/4	1/2	4/4	4/4	1/1	1/1	1/1	1/1	4/4	4/4	4/4	0/0	1/3	1/2	1/2	1/1																			
Acetic acid	C <sub>2</sub> H <sub>4</sub> O <sub>2</sub>	000064-19-7	10 %	Xi		1/1	1/1	4/4	1/2	1/1	3/0	1/4	1/1	1/1	1/0	1/3	1/0	1/3	1/1	1/1	1/1	1/1	(2)	(3)	3/3	0/0	1/3	1/1	1/1	1/1																			
Acetic acid	C <sub>2</sub> H <sub>4</sub> O <sub>2</sub>	000064-19-7	5 %	Xi		1/1	1/3	4/4	1/2	1/1	1/1	1/3	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/0	3/3	3/3	0/0	1/3	1/2	1/1	1/1	1/1																			
Acetic acid chloride	-> see: Acetyl chloride																																																
Acetic acid sodium salt	-> see: Sodium acetate																																																
Acetic aldehyde	-> see: Acetaldehyde																																																
Acetic anhydride	C <sub>2</sub> H <sub>4</sub> O <sub>3</sub>	000108-24-7	techn. pure	C	X	4/4	3/3	3/3	4/4	0/0	4/4	(2)	1/3	4/4	4/4	4/4	4/4	0/0	0/0	1/0	1/1	4/4	3/0	4/4	4/4	0/0	(2)	1/1	1/1	1/1																			
Acetic chloride	-> see: Acetyl chloride																																																
Acetone	C <sub>2</sub> H <sub>6</sub> O	000067-64-1		F, Xi	X	1/1	3/3	1/0	4/4	4/4	2/3	1/3	1/3	4/4	4/4	4/4	0/0	4/4	2/3	(1)	1/1	3/4	1/0	4/4	4/4	0/0	1/1	1/1	1/1	1/1	1/1	Propanone, 2-; Dimethyl ketone; Methyl ketone																	
Acetonitrile	C <sub>2</sub> H <sub>3</sub> N	000075-05-8		F, T	X	1/1	1/1	1/0	4/4	(4)	3/4	(3)	3/4	4/4	4/4	4/4	0/0	0/0	1/1	(1)	(1)	1/1	(3)	(3)	4/4	0/0	(1)	(1)	(1)	0/0	Methyl cyanide; Cyanomethane; Ethanitrile																		
Acetyl chloride	-> see: Chloroacetone																																																
Acetophenone	C <sub>8</sub> H <sub>8</sub> O	000098-86-2		Xn		0/0	1/0	1/0	(4)	(4)	(4)	1/0	1/3	0/4	0/0	4/4	4/4	0/4	1/1	0/0	1/1	1/3	1/0	4/4	4/4	0/0	1/1	(1)	(1)	0/0	Phenylethanone, 1-; Phenyl methyl ketone; Acetylbenzene																		
Acetyl chloride	C <sub>2</sub> H <sub>3</sub> ClO	000075-36-5	100 %	F, C	X	0/0	0/0	4/4	4/4	(4)	4/4	3/4	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/0	1/1	4/4	1/0	4/4	0/0	4/4	1/2L	1/1L	0/0	Acetic chloride; Ethanoyl chloride; Acetic acid chloride																		
Acetylene	C <sub>2</sub> H <sub>2</sub>	000074-86-2	100 %	F+	X	1/0	1/0	1/0	1/0	1/0	0/0	1/0	0/0	0/0	2/0	4/4	3/0	(1)	1/1	1/0	(1)	1/0	1/0	1/0	0/0	(1)	(1)	1/1	1/1	1/1	Ethine; Ethyne																		
Acetyloxybenzoic acid, 2-	-> see: Acetylsalicylic acid																																																
Acetylsalicylic acid	C <sub>9</sub> H <sub>8</sub> O <sub>4</sub>	000050-78-2	100 %	Xn		0/0	0/0	1/0	0/0	(2)	0/0	(3)	1/2	1/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/2	(2)	(3)	0/0	0/0	1/0	1/0	1/0	1/0	Acetyloxybenzoic acid, 2-;																		
Acrylonitrile	C <sub>3</sub> H <sub>3</sub> N	000107-13-1		F, T	X	1/1	1/3	1/0	4/4	(4)	3/4	(3)	3/4	4/4	4/4	4/4	0/0	1/2	1/1	1/0	3/3	4/4	4/4	4/4	0/0	1/0	1/0	1/0	1/1	1/1	Cyanoethylene; Propenenitrile, 2-; Vinyl cyanide																		
Adipic acid	C <sub>6</sub> H <sub>10</sub> O <sub>4</sub>	000124-04-9	saturated	Xi		1/1	1/2	0/0	1/1	(2)	1/1	1/3	1/1	1/1	2/2	1/3	1/3	0/0	1/1	1/1	1/1	1/0	1/0	1/0	1/1	0/0	1/0	(2)	(2)	1/1	Hexanedioic acid; Butanedicarboxylic acid, 1,4-																		
Alanine, L-	C <sub>3</sub> H <sub>7</sub> NO <sub>2</sub>	000056-41-7		—		1/1	1/1	1/1	4/4	(2)	1/1	1/1	1/1	4/4	4/4	0/0	0/0	1/1	1/1	1/1	(1)	1/0	(1)	(1)	0/0	(2)	(2)	(2)	(2)	Aminopropanoic acid, L-2; aminopropanoic acid, alpha-																			
Allspice	—	—	ground	?		0/0	0/0	(2)	4/4	0/0	(2)	4/4	0/0	0/0	0/0	0/0	3/3	0/0	(1)	(1)	(2)	(2)	(2)	0/0	(1)	(1)	(1)	(1)	(1)																				
Allyl acetate	C <sub>6</sub> H <sub>10</sub> O <sub>2</sub>	000591-87-7	100 %	F, T	X	0/0	1/3	4/4	4/4	(4)	(4)	(2)	1/3	4/4	0/0	0/0	4/4	0/0	0/0	(1)	1/1	(2)	(3)	4/4	4/4	0/0	(1)	(1)	(1)																				
Allyl alcohol	C <sub>3</sub> H <sub>6</sub> O	000107-18-6	96 %	F, T	X	1/3	3/3	3/0	3/3	1/0	1/2	(2)	2/2	2/4	2/3	2/3	4/4	4/4	1/1	1/1	(2)	1/0	4/4	3/0	0/0	1/1	1/1	1/1	1/1	1/1	Vinyl carbinol; Propenyl alcohol																		
Allyl chloride	C <sub>3</sub> H <sub>5</sub> Cl	000107-05-1	100 %	F, T+	X	(3)	3/4	0/0	(4)	(4)	(2)	4/4	0/0	0/0	4/4	0/0	0/0	(1)	(1)	(2)	1/1	4/4	(3)	4/4	0/0	1/0	(1L)	(1L)	0/0	Chloro-1-propene, 3-; Chloropropylene, 3-																			
Allyl mustard oil	C <sub>6</sub> H <sub>9</sub> NS	000057-06-7		T	X	0/0	0/0	0/0	(4)	(3)	(4)	(2)	(2)	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(2)	(3)	(3)	(4)	0/0	(1)	(1)	(1)		oleum sinapis																			
Almond oil, sweet	—	008007-69-0		—		0/0	0/0	(2)	(1)	1/0	0/0	(2)	3/4	0/0	0/0	0/0	1/1	0/0	(1)	1/1	1/1	4/4	(1)	(2)	0/0	(1)	1/1	1/1																					
Alumina acidic	C <sub>2</sub> H <sub>7</sub> AlO <sub>5</sub> x H <sub>2</sub> O	000142-03-0	saturated	Xi		1/1	1/0	(2)	(2)	0/0	1/0	1/1	0/0	1/0	1/0	1/0	1/1	1/1	1/1	(1)	1/0	4/4	3/3	0/0	(1)	1/1	1/1	1/1	1/1																				
Aluminium fluoride	AlF <sub>3</sub>	007789-18-1	aqueous	Xi		1/1	1/1	(3)	(2)	(2)	1/1	3/4	1/1	0/0	0/0	1/3	1/3	0/0	0/0	1/1	1/1	1/1	1/0	1/0	1/1	0/0	1/1	0/0	0/0	0/0																			
Aluminum ammonium sulfate dodecahydrate	(NH <sub>4</sub> ) <sub>2</sub> Al(SO <sub>4</sub> ) <sub>2</sub>	007784-26-1	saturated	Xi		1/1	1/1	3/4	(2)	(2)	0/0	3/4	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	1/0	(2)	1/1	0/0	1/0	1/2	1/3	0/0																			
Aluminum chloride	AlCl <sub>3</sub>	007784-13-6	10 %	?		1/1	1/2	1/0	1/0	(2)	1/1	3/4	1/1	0/0	1/1	0/0	1/1	0/0	1/1	2/2	1/1	1/1	1/1	1/0	1/0	1/0	0/0	4/4	4/4	3/4	1/1																		
Aluminum chloride	AlCl <sub>3</sub>	007784-13-6	solid	C		1/1	1/1	3/4	(3)	0/0	0/0	4/4	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(2)	(3)	(3)	(3)	0/0	4/4	4/4	3/4	1/1																				
Aluminum chloride	AlCl <sub>3</sub>	007784-13-6	saturated	C		1/1	1/1	3/4	(2)	0/0	0/0	4/4	1/1	0/0	0/0	1/1	0/0	1/1	0/0	1/1	(1)	1/1	(2)	1/0	1/1	0/0	4/4	4/4	3/4	1/1																			
Aluminum hydroxide	Al(OH) <sub>3</sub>	021645-51-2		Xi		1/1	1/2	1/1	1/1	1/1	1/2	1/1	1/2	2/2	2/2	1/2	1/1	1/1	1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	small solubility - no chemical effect expected																		
Aluminum nitrate	Al(NO <sub>3</sub> ) <sub>3</sub>	013473-90-0	aqueous	(O)		1/1	1/0	1/4	1/0	(2)	1/0	3/4	1/1	1/0	1/0	1/0	1/0	0/0	0/0	1/1	1/1	1/1	1/0	1/0	1/0	0/0	4/4	1/0	1/0	1/1																			
Aluminum oxide, alpha-	Al <sub>2</sub> O <sub>3</sub>	001344-28-1	solid	—		1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	small solubility - no chemical effect expected																		
Aluminum potassium sulfate	KAl(SO <sub>4</sub> ) <sub>2</sub> x 12H <sub>2</sub> O	010043-67-1	diluted	Xi		1/1	1/1	1/0	1/0	(2)	0/0	3/4	1/1	1/1	1/0	1/3	1/3	1/1	1/1	1/1	1/1	1/1	1/1	1/0	3/0	0/0	1/0	1/1	1/1	1/1																			
Aluminum potassium sulfate	KAl(SO <sub>4</sub> ) <sub>2</sub> x 12H <sub>2</sub> O	010043-67-1	saturated	Xi		1/1	1/1	1/0	1/0	(2)	0/0	3/4	1/1	1/0	1/0	1/3	1/3	0/0	1/1	1/1	1/1	1/1	1/1	1/0	3/3	0/0	1/0	(1)	(1)	0/0																			
Aluminum sodium sulfate	NaAl(SO <sub>4</sub> ) <sub>2</sub>	010102-71-3		?		1/1	1/1	(3)	(2)	(1)	0/0	(3)	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/0	(1)	(2)	0/0	1/3	(1)	(1)																				
Aluminum sulfate	Al <sub>2</sub> (SO <sub>4&lt;/</sub>																																																

CHEMICALS	FORMULA	CAS-NR.	CONCENTRATION	HAZARD NOTE	thermoplastics											fluoroplastics		elastomers		metals		COMMENT											
					FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HART	PVC WEICH	SAN	ECTFE / ETFE	FEP	PTFE		PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Haselloy C		
Ammonium chloride	(NH <sub>4</sub> )Cl	012125-02-9	solid	Xn		1/1	1/1	1/0	1/0	(2)	0/0	2/3	1/1	1/1	1/0	1/3	1/3	1/1	1/1	1/1	1/1	1/0	1/1	1/1	1/0	1/1	0/0	3/4	1/3L	1/2L	1/1	sal ammoniac	
Ammonium chloride	(NH <sub>4</sub> )Cl	012125-02-9	aqueous	Xn		1/1	1/1	1/0	1/0	(2)	1/1	2/3	1/1	1/1	1/0	1/3	1/3	1/1	1/1	1/1	1/1	1/0	1/1	1/1	0/0	3/4	1/3L	1/2L	1/1	sal ammoniac			
Ammonium difluoride	F <sub>2</sub> H <sub>3</sub> N	001341-49-7	50 %	T, C		1/1	1/1	2/0	(4)	0/0	0/0	(4)	1/1	0/0	0/0	1/3	0/0	0/0	0/0	1/1	1/1	1/1	1/0	(3)	2/3	0/0	(3)	1/0	1/0				
Ammonium ferric sulfate	(NH <sub>4</sub> )Fe(SO <sub>4</sub> ) <sub>2</sub>	007783-83-7	saturated	Xi		1/1	1/1	1/0	(2)	(2)	0/0	(3)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	1/0	(2)	(1)	0/0	(4)	0/0	0/0				
Ammonium ferrous sulfate	(NH <sub>4</sub> ) <sub>2</sub> Fe(SO <sub>4</sub> ) <sub>2</sub>	007783-85-9		Xi		1/1	1/1	(2)	(2)	(2)	0/0	(3)	1/1	1/1	0/0	0/0	0/0	1/1	1/1	1/1	1/1	(1)	(1)	(1)	0/0	4/4	(1)	(1)					
Ammonium fluoride	(NH <sub>4</sub> )F	012125-01-8	saturated	T, C		1/1	1/1	1/0	4/4	(2)	1/0	(2)	1/1	0/0	0/0	1/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	2/3	1/1	0/0	(4)	(1)	(1)	?			
Ammonium fluoride	(NH <sub>4</sub> )F	012125-01-8	aqueous	T, C		1/1	1/1	1/0	(3)	(2)	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	2/3	1/1	0/0	(4)	1/3	1/3	1/1				
Ammonium glycolate	C <sub>2</sub> H <sub>3</sub> NO <sub>2</sub>	035249-89-9		(Xi)		1/1	1/2	(1)	2/3	(2)	1/2	(2)	1/2	1/1	2/2	1/1	0/0	0/0	1/1	1/1	1/1	(1)	1/0	(3)	(1)	0/0	(2)	(2)	(2)		Acetic acid		
Ammonium heptamolybdate	(NH <sub>4</sub> ) <sub>6</sub> Mo <sub>7</sub> O <sub>24</sub>	012054-85-2		Xi		1/1	1/1	(1)	(2)	(2)	0/0	(1)	1/1	1/1	0/0	0/0	1/1	0/0	1/1	1/1	(1)	1/0	(3)	(1)	0/0	(1)	(1)	(1)	0/0				
Ammonium hydroxide	NH <sub>3</sub> + H <sub>2</sub> O	001336-21-6	30 %	C, N		1/1	1/2	(3)	4/4	2/4	1/2	1/2	2/3	2/3	1/2	2/3	2/3	1/2	0/0	0/0	1/1	1/1	(2)	1/0	(3)	2/3	0/0	1/1	1/1	1/1	1/1		
Ammonium hydroxide	NH <sub>3</sub> + H <sub>2</sub> O	001336-21-6	5 %	Xi		1/1	1/1	(2)	3/4	(2)	1/1	1/2	1/1	1/3	2/2	1/1	0/0	0/0	1/1	1/1	1/1	(2)	1/0	(2)	2/3	0/0	1/1	1/1	1/1	1/1			
Ammonium hydroxide	NH <sub>3</sub> + H <sub>2</sub> O	001336-21-6		C/Xi, N		1/1	1/1	(3)	4/4	2/4	1/1	1/2	1/1	2/3	2/3	1/2	1/3	2/2	1/1	1/1	1/1	1/3	1/0	(3)	4/4	0/0	1/1	1/1	1/1	1/1			
Ammonium mercaptan	-> see: Ammonium bisulfide																																
Ammonium nitrate	(NH <sub>4</sub> )NO <sub>3</sub>	006484-52-2	10 %	O		1/3	0/0	1/0	(1)	(2)	0/0	2/4	1/1	1/1	1/0	1/3	0/0	0/0	1/1	1/1	1/1	1/1	1/0	2/2	1/1	0/0	1/1	1/1	1/1	1/1	1/1	Nitric acid; Ammonium salt	
Ammonium nitrate	(NH <sub>4</sub> )NO <sub>3</sub>	006484-52-2	saturated	O		1/3	1/1	1/0	1/0	(2)	1/1	2/4	1/1	1/0	1/0	1/1	1/0	1/1	1/1	1/1	1/1	1/1	1/0	2/2	1/1	0/0	(2)	1/1	1/1	1/1			
Ammonium nitrite	(NH <sub>4</sub> )NO <sub>2</sub>	013446-48-5	aqueous	O, Xn		(1)	(1)	(2)	(2)	(2)	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	(3)	1/0	(2)	(1)	(1)						
Ammonium oxalate	C <sub>2</sub> H <sub>2</sub> N <sub>2</sub> O <sub>4</sub>	014258-49-2		Xn		1/1	1/2	(1)	1/1	(2)	1/2	(2)	1/2	1/1	1/1	1/1	0/0	0/0	1/1	1/1	1/1	(1)	1/0	(3)	(1)	0/0	1/1	1/1	1/1	0/0			
Ammonium persulfate	(NH <sub>4</sub> ) <sub>2</sub> S <sub>2</sub> O <sub>8</sub>	007727-54-0	saturated	O, Xn		0/0	0/0	4/4	(2)	0/0	0/0	(2)	1/1	0/0	0/0	1/0	0/0	0/0	1/1	1/1	1/1	1/0	(3)	4/4	0/0	4/4	(4)	3/4	0/0				
Ammonium persulfate	(NH <sub>4</sub> ) <sub>2</sub> S <sub>2</sub> O <sub>8</sub>	007727-54-0	aqueous	O, Xn		0/0	0/0	4/4	(2)	0/0	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	(3)	4/4	0/0	4/4	(4)	3/4	0/0				
Ammonium phosphate, Mono-	(NH <sub>4</sub> )H <sub>2</sub> PO <sub>4</sub>	007722-76-1	each	Xi		1/1	1/1	1/0	(2)	(2)	1/0	(2)	1/1	1/1	1/0	1/1	1/0	0/0	1/1	1/1	1/1	1/1	1/0	3/0	1/1	0/0	4/4	(1)	(1)	1/1			
Ammonium polyphosphate (APP)	(NH <sub>4</sub> PO <sub>3</sub> ) <sub>n</sub>	068333-79-9		Xi		1/1	1/1	(1)	(2)	(2)	0/0	(1)	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	(1)	1/0	(3)	1/1	0/0	(3)	(1)	(1)				
Ammonium rhodanide	-> see: Ammonium thiocyanate																																
Ammonium salt	-> see: Ammonium nitrate																																
Ammonium sulfate	(NH <sub>4</sub> ) <sub>2</sub> SO <sub>4</sub>	007783-20-2	10 %	Xn		1/1	1/1	1/0	1/1	(2)	(1)	1/0	1/1	1/1	1/0	1/3	0/0	0/0	1/1	1/1	1/1	1/1	1/0	2/3	1/1	0/0	1/1	1/1	1/1	1/1			
Ammonium sulfate	(NH <sub>4</sub> ) <sub>2</sub> SO <sub>4</sub>	007783-20-2	saturated	Xn		1/1	1/1	1/0	1/1	(2)	1/1	2/0	1/1	1/0	1/0	1/1	1/0	1/1	1/1	1/1	1/1	1/1	1/0	2/3	1/1	0/0	1/1	1/1	1/2	1/1			
Ammonium sulfide	(NH <sub>4</sub> ) <sub>2</sub> S	012135-76-1	each	T, C	X	1/1	1/1	1/0	4/4	0/0	1/1	(2)	1/1	0/0	0/0	1/3	1/0	0/0	0/0	1/1	1/1	1/1	1/0	(3)	1/2	0/0	1/1	(1)	(1)	?	Diammonium sulfide;		
Ammonium sulfide	(NH <sub>4</sub> ) <sub>2</sub> S	012135-76-1	aqueous	T, C	X	1/1	1/1	1/0	(3)	0/0	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	(3)	3/3	0/0	1/1	(1)	(1)	1/1				
Ammonium sulfocyanide	-> see: Ammonium thiocyanate																																
Ammonium thiocyanate	CH <sub>4</sub> N <sub>2</sub> S	001762-95-4		Xn		1/1	1/1	(3)	1/0	(2)	1/1	1/0	1/1	1/3	0/0	1/0	0/0	1/1	1/1	1/1	1/1	(1)	1/0	(3)	1/0	0/0	(2)	(1)	(1)		Ammonium sulfocyanide; Ammonium rhodanide; Thiocyanic acid, Ammonium salt; Ammonium sulfocyanate		
Amomum	—	—		?		0/0	0/0	(2)	(2)	(2)	0/0	(2)	(2)	4/4	0/0	0/0	0/0	1/1	0/0	(1)	(1)	(1)	(2)	(1)	(2)	0/0	(1)	(1)	(1)				
Amyl acetate, normal	C <sub>7</sub> H <sub>14</sub> O <sub>2</sub>	000628-63-7		—	X	1/2	2/3	2/0	4/4	1/3	2/3	(1)	3/4	4/4	4/4	4/4	4/4	4/4	1/1	1/1	1/1	1/3	3/4	4/4	4/4	0/0	1/1	1/1	1/1	0/0			
Amyl alcohol, n-	-> see: Pentanol, 1-																																
Amyl chloride	C <sub>8</sub> H <sub>17</sub> Cl	000543-59-9		F, Xn	X	3/4	4/4	1/0	4/4	0/0	4/4	(2)	4/4	4/4	4/4	4/4	4/4	0/0	1/1	1/1	1/1	1/1	4/4	1/0	4/4	0/0	3/4	3/4L	3/4L	0/0			
Amyl cinnamic aldehyde	C <sub>14</sub> H <sub>16</sub> O	000122-40-7		Xi		0/0	0/0	0/0	(4)	0/0	(4)	(3)	(3)	0/0	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(2)	(4)	(3)	(4)	0/0	(1)	(1)	(1)		odoriferous substance		
Aniline	C <sub>6</sub> H <sub>5</sub> N	000062-53-3		T		1/2	1/3	3/4	4/4	0/0	2/3	1/3	2/3	4/4	4/4	4/4	4/4	0/4	2/4	1/1	1/1	1/4	4/4	2/4	4/4	0/0	1/0	1/0	1/0	1/1			
Aniline hydrochloride	C <sub>6</sub> H <sub>5</sub> ClN	000142-04-1	saturated	T		1/3	0/0	(3)	(3)	0/0	0/0	(3)	1/3	0/0	0/0	1/0	0/0	0/0	1/1	1/1	1/1	3/0	2/2	3/3	0/0	4/4	4/4	4/4					
Anise	—	—		?		0/0	0/0	(2)	(2)	(2)	0/0	(2)	(2)	0/0	0/0	0/0	0/0	1/1	0/0	1/1	(1)	(1)	(2)	(2)	(2)	0/0	(1)	(1)	(1)				
Anise oil	—	084775-42-8		Xi		0/0	0/0	(3)	(3)	0/0	(4)	(2)	(3)	0/0	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(3)	4/4	(3)	4/4	0/0	(1)	(1)	(1)	0/0			
Anisole	C <sub>7</sub> H <sub>8</sub> O	000100-66-3	100 %	Xi	X	1/4	3/4	1/0	4/4	0/0	2/3	(2)	3/3	4/4	0/0	0/0	0/0	0/0	1/1	1/1	(3)	4/4	4/4	4/4	0/0	1/0	(1)	(1)	0/0				
Antifreeze agent (car)	—	—		Xn		1/1	1/1	3/3	(1)	1/0	0/0	1/1	1/1	1/1	0/0	0/0	0/0	0/0	(1)	1/0	1/1	1/0	1/2	1/1	0/0	(1)	1/1	1/1		glycol-water-mixture			
Antimony pentachloride	SbCl <sub>5</sub>	007647-18-9		C		0/0	0/0	4/4	(3)	0/0	0/0	4/4	1/1	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(2)	(2)	(2)	4/4	0/0	(3)	(4)	0/0					
Antimony trichloride	SbCl <sub>3</sub>	010025-91-9	90 %	C		1/1	1/1	4/4	1/0	0/0	0/0	4/4	1/1	0/0	0/0	1/0	0/0	0/0	1/1	1/1	1/1	1/0	1/										



CHEMICALS	FORMULA	CAS-NR.	CONCENTRATION	HAZARD NOTE	FLAMMABLE	thermoplastics														fluoroplastics		elastomers		metals		COMMENT					
						HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HART	PVC WEICH	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FKM / FKM	NBR		SI	AL	V2A	V4A	Hastelloy C
Butter	—	—	—	—	—	1/0	1/0	1/0	1/0	1/0	1/0	1/1	1/1	1/1	0/0	0/0	0/0	1/1	0/0	1/1	1/1	(1)	3/0	1/0	1/1	0/0	(1)	(1)	(1)		
Butyl acetate, normal	C <sub>8</sub> H <sub>16</sub> O <sub>2</sub>	000123-86-4	100 %	—	X	2/2	2/3	1/0	4/4	3/0	3/3	(2)	3/4	4/4	4/4	4/4	4/4	1/2	1/1	1/1	1/4	3/0	4/4	4/4	0/0	1/1	(1)	(1)	4/4		
Butyl acrylate	C <sub>8</sub> H <sub>12</sub> O <sub>2</sub>	000141-32-2	100 %	Xi	X	1/2	2/3	2/0	4/4	1/3	2/3	(2)	3/4	4/4	4/4	4/4	4/4	1/1	1/1	1/1	1/3	4/4	4/4	4/4	0/0	1/1	1/1	1/1	1/0		
Butyl alcohol, normal	C <sub>4</sub> H <sub>10</sub> O	000071-36-3	techn. pure	Xn	X	1/1	1/3	1/0	2/3	1/0	1/2	1/2	1/2	1/2	2/3	2/3	4/4	1/3	1/1	1/1	1/1	2/0	3/4	1/0	0/0	1/1	(1)	(1)	0/0	Propyl carbinol; Butanol	
Butyl alcohol, sec-	C <sub>4</sub> H <sub>10</sub> O	000078-92-2	—	Xn	X	1/1	1/2	(1)	2/3	1/0	1/2	(1)	1/2	2/2	2/3	2/2	0/0	0/0	1/1	1/1	1/1	3/0	(1)	(2)	0/0	1/1	(1)	(1)		Butanol, -2; Methyl ethyl carbinol; Butylene hydrate	
Butyl alcohol, tert-	C <sub>4</sub> H <sub>10</sub> O	000075-65-0	—	F, Xn	X	1/1	1/2	(1)	2/3	1/0	1/2	(1)	1/2	1/1	2/3	1/2	0/0	0/0	1/1	1/1	1/1	3/0	(1)	(2)	0/0	1/1	(1)	(1)			
Butyl aldehyde	-> see: Butyraldehyde																														
Butyl carbinol, n-	-> see: Pentanol, 1-																														
Butyl ether, (Di-) n-	C <sub>8</sub> H <sub>18</sub> O	000142-96-1	techn. pure	Xi	X	3/4	1/4	(2)	(3)	1/0	(4)	(1)	3/4	0/0	3/0	4/4	0/0	0/0	(1)	1/1	1/1	4/4	4/4	4/4	0/0	1/1	(1)	(1)	0/0	Butoxybutane, 1-;	
Butyl ethylene	-> see: Hexene, 1-																														
Butyl stearate	C <sub>22</sub> H <sub>44</sub> O <sub>2</sub>	000123-95-5	100 %	Xi	—	0/0	0/0	(1)	(3)	1/0	0/0	(2)	(2)	0/0	0/0	1/0	1/0	0/0	(1)	(1)	(1)	4/4	1/0	4/4	0/0	(1)	1/1	1/1	0/0		
Butylamine	C <sub>4</sub> H <sub>11</sub> N	000109-73-9	—	F, C	X	0/0	0/0	0/0	(3)	0/0	0/0	3/4	2/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	4/4	4/4	0/0	(1)	(1)	0/0			
Butylene glycol	C <sub>4</sub> H <sub>10</sub> O <sub>2</sub>	—	techn. pure	—	—	1/1	1/1	1/0	1/0	1/0	0/0	1/1	0/0	0/0	1/3	0/0	0/0	0/0	1/1	1/1	1/1	1/0	4/4	(1)	0/0	1/1	(1)	0/0		isomer not indicated in the source	
Butylene hydrate	-> see: Butyl alcohol, sec-																														
Butylphenol	C <sub>10</sub> H <sub>14</sub> O	—	100 %	Xi	—	0/0	1/1	(3)	(3)	0/0	(3)	(4)	1/1	0/0	0/0	3/4	4/4	0/0	(1)	1/1	1/1	4/4	3/0	4/4	0/0	1/1	1/1	1/1	1/1	isomer not indicated in the source	
Butylphenol, p-tert	C <sub>11</sub> H <sub>16</sub> NO	000098-54-4	techn. pure	C, Xn	—	3/0	0/0	(3)	(3)	0/0	(3)	(4)	1/0	0/0	0/0	3/0	0/0	0/0	(1)	1/0	1/1	4/4	3/0	4/4	0/0	1/1	1/1	1/1			
Butyraldehyde	C <sub>4</sub> H <sub>8</sub> O	000123-72-8	—	F, Xn	X	0/0	0/0	(3)	(3)	0/0	(4)	(2)	(2)	0/0	0/0	0/0	0/0	0/0	(1)	(2)	(3)	3/0	4/4	4/4	0/0	(1)	(1)	(1)		Butanal; Butyl aldehyde	
Butyric acid	C <sub>4</sub> H <sub>8</sub> O <sub>2</sub>	000107-92-6	—	C	—	3/4	4/4	3/3	4/4	0/0	4/4	4/4	4/4	2/2	2/4	4/4	4/4	1/1	1/1	1/1	1/1	4/4	3/4	4/4	0/0	1/2	1/2	1/1	1/1		
Cadmium bromide	CdBr	007789-42-6	—	T	—	1/1	1/1	(3)	(2)	(2)	0/0	(3)	(1)	1/1	0/0	0/0	1/1	0/0	1/1	1/1	(1)	(2)	(2)	(2)	0/0	4/4	0/0	0/0			
Calcium bicarbonate	Ca(HCO <sub>3</sub> ) <sub>2</sub>	—	saturated	—	—	1/1	1/1	1/1	(1)	(1)	0/0	1/1	1/1	0/0	0/0	1/0	1/0	0/0	1/1	1/1	1/1	1/0	(1)	(1)	0/0	(2)	(1)	(1)	0/0		
Calcium bisulfite	Ca(HSO <sub>3</sub> ) <sub>2</sub>	013780-03-5	saturated	Xn	—	1/1	1/1	(3)	(2)	0/0	0/0	4/4	1/1	0/0	0/0	1/0	0/0	0/0	1/1	1/1	1/1	4/4	1/0	3/3	0/0	(3)	1/1	1/3	1/1		
Calcium bisulfite	Ca(HSO <sub>3</sub> ) <sub>2</sub>	013780-03-5	aqueous	Xn	—	1/1	1/1	(3)	(2)	0/0	0/0	4/4	1/1	0/0	0/0	0/0	0/0	1/1	1/1	1/1	4/4	1/0	3/3	0/0	(3)	1/1	1/3	1/1			
Calcium bromide	CaBr <sub>2</sub>	007789-41-5	—	?	—	1/1	1/1	(2)	(1)	(2)	0/0	(3)	1/1	1/1	0/0	0/0	0/0	1/1	1/1	1/1	1/1	(1)	(1)	(1)	0/0	(3)	0/0	0/0	0/0		
Calcium carbide	CaC <sub>2</sub>	000075-20-7	—	F	X	1/1	1/1	(2)	(2)	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	(1)	1/1	(1)	(2)	(2)	(2)	0/0	(3)	(1)	(1)	0/0	carbide, reacts with water to acetylene - highly flammable!		
Calcium carbonate	CaCO <sub>3</sub>	000471-34-1	saturated	—	—	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	small solubility - no chemical effect expected	
Calcium chlorate	Ca(ClO <sub>3</sub> ) <sub>2</sub>	010137-74-3	saturated	O, (T)	—	0/0	0/0	(3)	(2)	0/0	1/1	(3)	1/1	0/0	0/0	0/0	0/0	0/0	1/1	(1)	1/1	(2)	(1)	(3)	0/0	1/1	(1)	1/0	1/1		
Calcium chloride	CaCl <sub>2</sub>	010043-52-4	alkoholic	F, Xi	—	1/0	0/0	4/4	(2)	0/0	1/0	(3)	1/1	0/0	0/0	0/0	4/4	0/0	0/0	1/1	1/0	(1)	(2)	(2)	(2)	0/0	(3)	1/2L	1/2L	1/1	
Calcium chloride	CaCl <sub>2</sub>	010043-52-4	aqueous	Xi	—	1/1	1/1	1/0	1/0	1/1	(3)	1/1	1/1	1/0	1/3	1/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	3/3	1/2L	1/2L	1/1			
Calcium hydroxyde	CaH <sub>2</sub> O <sub>2</sub>	001305-62-0	aqueous	(Xi)	—	1/1	1/1	1/0	4/4	1/0	1/1	1/1	1/1	1/1	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/1	1/0	0/0	3/4	1/1	1/1	0/0		
Calcium hydroxyde	CaH <sub>2</sub> O <sub>2</sub>	001305-62-0	concentrated	C	—	1/1	1/1	1/0	4/4	1/0	1/1	1/1	1/1	2/2	2/2	1/1	1/0	0/0	1/1	1/1	1/1	1/3	1/0	1/1	1/0	0/0	3/4	1/1	1/1	0/0	
Calcium hypochlorite	Ca(OCl) <sub>2</sub>	007778-54-3	saturated	O, C	—	1/1	1/1	1/4	3/4	3/0	1/2	1/0	1/1	2/3	1/1	2/3	3/0	1/1	1/1	1/1	1/3	(2)	2/3	4/4	0/0	4/4	3/0	2/0	1/1	bleaching powder	
Calcium hypochlorite	Ca(OCl) <sub>2</sub>	007778-54-3	aqueous	O, C/Xi	—	0/0	0/0	4/4	1/0	3/0	0/0	1/0	1/1	1/3	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	2/3	4/4	0/0	4/4	3/0	2/0	1/1	bleaching powder	
Calcium nitrate	Ca(NO <sub>3</sub> ) <sub>2</sub>	010124-37-5	50 %	O	—	1/1	1/1	(2)	1/0	(2)	1/1	(3)	1/1	1/1	0/0	1/0	1/0	0/0	1/1	1/1	1/1	1/0	1/0	4/4	0/0	1/0	1/1	1/1	1/1		
Calcium nitrate	Ca(NO <sub>3</sub> ) <sub>2</sub>	010124-37-5	aqueous	O	—	1/1	1/1	(2)	(1)	(2)	0/0	(3)	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/0	1/1	0/0	1/0	1/1	1/1	1/1		
Calcium oxide	CaO	001305-78-8	powder	C	—	1/0	1/1	(2)	(2)	(2)	0/0	0/0	1/1	1/1	0/0	1/0	1/0	1/1	1/1	1/1	(1)	1/0	1/0	1/0	0/0	(3)	1/1	1/1			
Calcium phosphate	Ca <sub>3</sub> (PO <sub>4</sub> ) <sub>2</sub>	007758-87-4	aqueous	—	—	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	small solubility - no chemical effect expected	
Calcium phosphate	Ca <sub>3</sub> (PO <sub>4</sub> ) <sub>2</sub>	007758-87-4	—	—	—	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	small solubility - no chemical effect expected	
Calcium sulfate	CaSO <sub>4</sub>	007778-18-9	saturated	—	—	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/3	1/1	0/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	1/1	1/1	1/1	0/0	plaster
Calcium sulfide	CaS	020548-54-3	aqueous	C	—	0/0	0/0	(2)	(2)	0/0	0/0	(1)	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/0	1/0	0/0	1/0	(1)	(1)	0/0		
Calcium sulfide	CaS	020548-54-3	—	C	—	0/0	3/3	(2)	(2)	0/0	(1)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/0	3/3	0/0	1/0	(1)	(1)	0/0		
Calciumacetat	C <sub>2</sub> H <sub>4</sub> CaO <sub>4</sub>	000062-54-4	aqueous	—	—	1/1	1/1	(2)	(1)	(2)	0/0	(1)	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	(1)	1/0	4/4	3/3	0/0	(2)	(1)	(1)	0/0	
Camphor	C <sub>10</sub> H <sub>16</sub> O	000464-48-2 / -49-2	—	F, Xn	X	3/4	3/4	(2)	(3)	0/0	0/0	(2)	1/0	1/3	0/0	4/4	4/4	1/1	0/0	(1)	1/0	(3)	4/4	3/4	1/0	0/0	(1)	1/0	1/0	1/0	
Camphor oil	—	008008-51-3	—	Xn	—	4/4	4/4	(2)	(3)	0/0	0/0	(2)	4/4	0/0	0/0	4/4	4/4	0/0	(1)	(2)	(3)	4/4	3/0	1/0	0/0	(1)	(1)	1/0	1/0	from cinnamomum camphora	
Caprylic alcohol	C <sub>8</sub> H <sub>16</sub> O	000111-87-5	—	Xi	—	0/0	0/0	(2)	(2)	(1)	0/0	(2)	(2)	0/0	0/0	0/0	0/0	1/1	0/0	(1)	(1)	(1)	1/0	1/0	3/3	0/0	(1)	(1)	(1)		
Caraway	—	—	ground	?	—	0/0	0/0	(2)	(2)	(1)	0/0	1/1	(2)	4/4	0/0	0/0	0/0	1/1	0/0	(1)	(1)	(1)	(2)	(1)	(						

CHEMICALS	FORMULA	CAS-NR.	CONCENTRATION	HAZARD NOTE	thermoplastics																	fluoroplastics			elastomers			metals		COMMENT	
					FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HART	PVC WEICH	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A		Hastelloy C
Carbon tetrachloride (TETRA)	CCl <sub>4</sub>	000056-23-5		T	4/4	4/4	4/4	4/4	4/4	1/4	4/4	2/3	4/4	4/4	4/4	4/4	4/4	4/4	1/1	1/1	1/1	1/3	4/4	1/1	4/4	0/0	4/4	(1/1L) <sup>1)</sup>	(1/1L) <sup>1)</sup>	1/1	<sup>1)</sup> Water-free! If even traces of hydrochloric acid (HCl) are split off by moisture, there is a risk of pitting, crevice and stress corrosion cracking.
Carbon tetrafluoride	CF <sub>4</sub>	000075-73-0		?	0/0	0/0	1/0	(3)	0/0	0/0	1/0	(3)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	0/0	1/0	3/0	1/0	0/0	(3)	0/0	0/0			
Carbonyl chloride	-> see: Phosgene																														
Carnauba wax	—	008015-86-9		—	1/1	1/1	1/1	(1)	1/0	0/0	(1)	1/1	0/0	0/0	0/0	0/0	1/1	0/0	1/1	1/1	(1)	(3)	(1)	(1)	0/0	1/1	(1)	(1)			
Castor oil	—	008001-79-4	100 %	Xi	1/1	1/1	1/0	1/0	(1)	1/0	(2)	1/1	1/1	0/0	1/0	3/0	1/1	0/0	(1)	1/1	1/1	3/0	1/0	1/0	0/0	(1)	1/1	1/1	1/1		
Caustic potash	-> see: Potassium hydroxide																														
Cedar wood oil	—	008000-27-9		?	3/4	4/4	(2)	2/3	0/0	4/4	(2)	4/4	4/4	3/3	3/4	0/0	0/0	1/2	1/1	(1)	(2)	(4)	(2)	(3)	0/0	(1)	(1)	(1)			
Cesium bromide	CsBr	007787-69-1		Xi	1/1	1/1	(2)	(2)	(2)	0/0	(1)	1/1	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	(1)	(1)	(2)	(1)	0/0	(2)	0/0	0/0			
Cetyl alcohol	C <sub>18</sub> H <sub>38</sub> O	036653-82-4	100 %	Xi	1/1	1/1	4/4	(2)	1/0	0/0	(1)	1/1	0/0	1/0	1/1	3/3	1/1	1/1	1/1	1/1	1/1	1/0	1/0	1/0	0/0	(1)	1/1	1/1			
Chalk	CaCO <sub>3</sub>	—		—	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	calcium carbonate
Chloral hydrate	C <sub>2</sub> H <sub>3</sub> Cl <sub>3</sub> O <sub>2</sub>	000302-17-0	techn. pure	T/Xi	3/3	3/3	4/4	(3)	(4)	0/0	(3)	3/4	0/0	0/0	4/4	4/4	0/0	0/0	(1)	1/1	4/4	3/0	3/4	4/4	0/0	4/4	0/0	0/0	0/0		
Chloramine-T	C <sub>2</sub> H <sub>3</sub> ClN <sub>3</sub> NaSO <sub>2</sub>	000127-65-1	diluted	Xi	1/0	1/0	4/4	1/0	0/0	(3)	(3)	0/0	0/0	0/0	1/0	0/0	0/0	(1)	1/0	3/4	1/0	4/4	1/0	0/0	3/4	2/2	1/1	0/0			
Chloric acid	HClO <sub>3</sub>	007790-93-4	1 %	(C)	0/0	1/1	4/4	(3)	0/0	0/0	(3)	1/3	0/0	0/0	1/3	0/0	0/0	0/0	1/1	1/1	3/0	1/1	(3)	0/0	(3)	4/4	4/4	1/1			
Chloric acid	HClO <sub>3</sub>	007790-93-4	10 %	(O), C	1/0	0/0	4/4	(3)	0/0	0/0	4/4	4/4	0/0	0/0	1/3	0/0	0/0	0/0	0/0	1/1	1/1	3/0	3/0	4/4	0/0	4/4	4/4	4/4	1/1		
Chloric acid	HClO <sub>3</sub>	007790-93-4	20 %	(O), C	3/0	1/4	4/4	(3)	(4)	0/0	4/4	1/4	0/0	0/0	1/3	0/0	0/0	0/0	0/0	1/1	1/0	3/0	3/0	4/4	0/0	4/4	4/4	4/4	?		
Chloric acid, sodium salt	-> see: Sodium chlorate																														
Chlorine	Cl <sub>2</sub>	007782-50-5	10 % wet	T	3/4	3/4	4/4	2/3	4/4	2/4	4/4	4/4	4/4	4/4	1/2	0/0	4/4	1/1	1/1	1/1	(2)	2/0	3/0	4/4	0/0	4/4	4/4	4/4	0/0		
Chlorine	Cl <sub>2</sub>	007782-50-5	97 %	T	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	0/0	1/1	1/0	1/1	4/4	1/1	4/4	0/0	(3)	1/0	1/0	1/1		
Chlorine	Cl <sub>2</sub>	007782-50-5	steam	T	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	0/0	1/1	1/0	1/1	4/4	1/1	4/4	0/0	(3)	1/0	1/0			
Chlorine dioxide	ClO <sub>2</sub>	010049-04-4		E, T	0/0	0/0	4/4	(3)	0/0	0/0	(3)	(3)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	1/0	(2)	4/4	1/0	4/4	0/0	3/4	3/4	3/4			
Chlorine trifluoride	ClF <sub>3</sub>	007790-91-2		(O, T)	0/0	0/0	4/4	(4)	4/4	(4)	4/4	(4)	0/0	0/0	0/0	0/0	0/0	0/0	(2)	(4)	4/4	(4)	4/4	0/0	(4)	(4)	(4)				
Chlorine water	Cl <sub>2</sub> x H <sub>2</sub> O	007782-50-5		(T)	3/0	0/4	4/4	4/4	4/4	4/4	4/4	3/4	4/4	0/0	3/3	1/1	(1)	1/1	1/1	3/0	1/0	4/4	0/0	4/4	2/0L	2/0L	0/0				
Chloro acetophenone, p-	C <sub>8</sub> H <sub>7</sub> ClO	000099-91-2		(Xn)	1/1	1/1	(2)	4/4	0/0	1/1	(2)	1/1	4/4	4/4	4/4	0/0	0/0	1/1	1/1	(2)	(2)	(3)	4/4	4/4	0/0	(1)	0/0	0/0			
Chloro-1-propene, 3-	-> see: Allyl chloride																														
Chloro-2-propanone, 1-	-> see: Chloroacetone																														
Chloroacetic acid	C <sub>2</sub> H <sub>3</sub> ClO <sub>2</sub>	000079-11-8	50 %	T, C	1/3	1/3	4/4	(4)	4/4	0/0	4/4	1/1	0/0	0/0	1/0	0/0	3/4	0/0	(1)	1/1	1/4	2/0	3/0	4/4	0/0	4/4	2/4	2/4	1/4		
Chloroacetic acid	C <sub>2</sub> H <sub>3</sub> ClO <sub>2</sub>	000079-11-8		T, C	1/1	1/1	4/4	3/4	4/4	1/2	4/4	1/2	2/4	4/4	3/4	4/4	3/4	1/1	1/1	1/1	4/4	3/0	3/0	4/4	0/0	4/4	4/4	4/4	4/4		
Chloroacetone	C <sub>3</sub> H <sub>5</sub> ClO	000078-95-5		(F, Xi)	X	0/0	0/0	(3)	(4)	(4)	(4)	(3)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(2)	(3)	1/0	4/4	4/4	0/0	(4)	0/0	0/0	0/0		Chloro-2-propanone, 1-; Acetyl chloride; Monochloroacetone
Chlorobenzene	C <sub>6</sub> H <sub>5</sub> Cl	000108-90-7		Xn	X	3/4	3/4	4/4	4/4	1/4	4/4	1/0	3/4	4/4	4/4	4/4	4/4	1/1	1/1	1/1	1/1	4/4	3/4	4/4	0/0	1/1	(1/1) <sup>1)</sup>	(1/1) <sup>1)</sup>	1/1	Benzene chloride; Chlorobenzol; Monochlorobenzene (MCB); Phenyl chloride <sup>1)</sup> Water-free! If even traces of hydrochloric acid (HCl) are split off by moisture, there is a risk of pitting, crevice and stress corrosion cracking.	
Chlorodifluoroethane	C <sub>2</sub> H <sub>2</sub> ClF <sub>2</sub>	000075-68-3		?	0/0	0/0	1/0	(3)	0/0	0/0	1/0	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	0/0	1/0	4/4	1/0	0/0	(3)	0/0	0/0				
Chlorodifluoromethane	CHClF <sub>2</sub>	000075-45-6		N, Xn	0/0	3/0	1/0	3/0	1/0	0/0	1/0	4/4	4/4	4/4	2/0	4/4	0/0	0/0	3/3	1/0	(3)	1/0	4/4	4/4	0/0	(3)	0/0	0/0			R 22
Chloroethane, 1-	-> see: Monochloroethane																														
Chloroethyl alcohol, 2-	C <sub>2</sub> H <sub>4</sub> ClO	000107-07-3	techn. pure	T+	1/1	0/0	4/4	4/4	0/0	0/0	3/4	4/4	0/0	0/0	4/4	0/0	0/0	0/0	1/1	1/0	1/3	3/0	4/4	4/4	0/0	(3)	1/0L	1/0L	1/0		
Chloroethylene	-> see: Vinyl chloride (VCM)																														
Chlorofluorocarbons (CFC)	—	—		N	0/0	0/0	(2)	(3)	0/0	0/0	1/0	(3)	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(3)	(3)	0/0	(3)	0/0	(3)	0/0	0/0				resistance depends on type
Chlorofluoromethane	CH <sub>2</sub> ClF	000593-70-4		N	0/0	0/0	1/0	(3)	0/0	0/0	1/0	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	0/0	1/0	4/4	4/4	0/0	(3)	0/0	0/0				
Chloroform	CHCl <sub>3</sub>	000067-66-3	100 %	Xn	3/4	4/4	3/4	4/4	4/4	4/4	4/4	3/4	4/4	4/4	4/4	4/4	4/4	2/3	1/1	1/1	1/1	4/4	3/4	4/4	0/0	(3)	(1/1) <sup>1)</sup>	(1/1) <sup>1)</sup>	1/1	<sup>1)</sup> Water-free! If even traces of hydrochloric acid (HCl) are split off by moisture, there is a risk of pitting, crevice and stress corrosion cracking.	
Chloroformyl chloride	-> see: Phosgene																														
Chloronaphthalene, 1-	C <sub>10</sub> H <sub>7</sub> Cl	000090-13-1		Xn	0/0	0/0	(2)	(3)	0/0	0/0	(2)	4/4	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	1/1	4/4	1/0	4/4	0/0	(2)	1/0	1/0			
Chloropentafluoroethane	C <sub>2</sub> ClF <sub>5</sub>	000076-15-3		?	0/0	0/0	1/0	(3)	0/0	0/0	1/0	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	0/0	1/0	3/0	1/0	0/0	(3)	0/0	0/0				
Chloroprene	C <sub>4</sub> H <sub>5</sub> Cl	000126-99-8		F, Xn	X	0/0	0/0	(2)	(3)	0/0	(4)	(2)	(3)	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	3/4	4/4	0/0	(3)	0/0	0/0			
Chloropropylene, 3-	-> see: Allyl chloride																														
Chlorosulfonic acid	ClHSO <sub>3</sub>	007790-94-5	techn. pure	C+	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	3/0	4/4	4/4	0/0	0/0	1/0	3/4	4/4	4/4	4/4	0/0	3/3	3/4	3/4	1/0		
Chlorotoluene	C <sub>7</sub> H <sub>7</sub> Cl	—		Xn	0/0	0/0	(2)	4/4	0/0	(4)	(1)	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/0	1/1	4/4	1/0	4/4	0/0	(3)	1/0	1/0	1/1		isomer not indicated in the source
Chlorotrifluoromethane	CClF <sub>3</sub>	000075-72-9		?	0/0	0/0	1/0	(3)	0/0	0/0	1/0	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	0/0	1/0	3/0	1/0	0/0	(3)	0/0	0/0				
Chromic acid	CrO <sub>3</sub>	001333-82-0	10 %	O, T, C, N	1/1	1/1	4/4	2/3	3/0	1/1	4/4	1/1	1/1	4/4	1/2	0/0	0/3	1/1	1/1	1/1	1/1	4/4	1/1	4/4	0/0	1/3	1/2	1/2	1/1	Chromium trioxide;	
Chromic acid	CrO <sub>3</sub>	001333-82-0	20 %	O, T, C, N	0/0	1/3	4/4	3/4	(4)	0/0	4/4	3/3	1/0	1/0	1/0	1/0	0/0	0/0	1/1	1/1	1/1	4/4	1/1	4/4	0/0	1/3	(2)	(2)	1/1		

CHEMICALS	FORMULA	CAS-NR.	CONCENTRATION	HAZARD NOTE	FLAMMABLE	thermoplastics														fluoroplastics		elastomers		metals		COMMENT																					
						HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HART	PVC WEICH	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR		SI	AL	V2A	V4A	Hastelloy C																
Chromic acid	CrO <sub>3</sub>	001333-82-0	50 %	O, T, C, N		3/4	3/4	4/4	3/4	(4)	2/3	4/4	3/3	3/3	4/4	1/3	1/0	3/3	1/1	1/1	1/1	1/1	4/4	1/0	4/4	0/0	(3)	2/3	2/3	1/1																	
Chromic potassium sulfate	KCr(SO <sub>4</sub> ) <sub>2</sub> x 12H <sub>2</sub> O	007788-99-0	saturated	Xn		1/1	0/0	(2)	1/0	(2)	0/0	(3)	1/1	0/0	0/0	1/1	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/0	1/1	0/0	(3)	1/3	1/3	1/1																	
Chromic-sulfuric acid	CrO <sub>3</sub> + H <sub>2</sub> SO <sub>4</sub>	065272-71-1	concentrated	O, T, C, N		4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	0/0	0/0	4/4	4/4	1/1	0/0	1/1	4/4	4/4	1/0	4/4	4/4	4/4	2/3	2/3	0/0																	
Chromium salts	—	—	each	T/Xn		0/0	0/0	0/0	(2)	(2)	0/0	(3)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	(1)	(1)	(1)	0/0	K	K	K																	
Chromium trioxide	-> see: Chromic acid																																														
Cinnamaldehyde	C <sub>9</sub> H <sub>8</sub> O	000104-55-2		Xn, Xi		0/0	0/0	(2)	(3)	0/0	(4)	(2)	(3)	4/4	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(2)	1/0	1/0	4/4	0/0	(1)	(1)	(1)																		
Cinnamon	—	—	ground	?		0/0	0/0	(2)	1/0	(2)	0/0	(2)	(2)	3/0	0/0	0/0	0/0	1/1	0/0	(1)	(1)	(1)	(2)	(2)	(2)	0/0	(1)	(1)																			
Cinnamon oil	—	008007-80-5		Xn, Xi		3/4	4/4	(2)	2/3	0/0	4/4	(2)	4/4	4/4	3/3	4/4	0/0	0/0	1/2	1/1	(1)	(2)	(3)	(3)	4/4	0/0	(1)	(1)	(1)																		
Citric acid	C <sub>6</sub> H <sub>8</sub> O <sub>7</sub>	000077-92-9	10 %	Xi		1/1	1/1	1/1	1/2	1/3	1/1	2/4	1/1	1/2	1/1	1/3	1/0	1/1	1/1	1/1	1/1	1/1	1/0	1/1	1/1	0/0	1/0	1/1	1/1	1/1																	
Citric acid	C <sub>6</sub> H <sub>8</sub> O <sub>7</sub>	000077-92-9	50 %	Xi		1/1	1/1	3/0	1/0	0/0	1/0	2/0	1/1	1/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	(1)	1/1	0/0	1/0	1/3	1/2	1/1																	
Citric acid	C <sub>6</sub> H <sub>8</sub> O <sub>7</sub>	000077-92-9	saturated	Xi		1/1	1/1	3/0	1/0	0/0	1/0	2/0	1/1	1/1	0/0	1/1	1/1	0/0	0/0	1/1	1/1	1/1	1/0	(1)	1/1	0/0	1/0	1/3	1/2	1/1																	
Citrus juices	—	—	aqueous	—		1/1	1/1	1/0	1/0	1/0	0/0	1/0	1/1	0/0	0/0	1/1	1/1	0/0	0/0	1/1	1/1	1/1	(1)	1/0	1/1	0/0	(2)	1/1	1/1																		
Cleaning agents	—	—	—	?		1/1	1/1	1/0	1/0	0/0	1/1	0/0	0/0	1/3	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	(1)	1/0	1/1	(2)	0/0	1/1	1/1																		
Clophen A60	—	011096-82-5		Xn, N		0/0	0/0	1/0	(3)	0/0	0/0	(2)	4/4	0/0	0/0	4/4	0/0	0/0	0/0	0/0	(1)	(2)	4/4	2/3	4/4	0/0	1/0	1/0	1/0	0/0	polychlorinated Biphenyls, PCB; Bayer																
Coal gas, without benzene	—	—		F+, T	X	1/0	1/0	1/0	1/0	(2)	1/0	(2)	1/0	1/0	0/0	1/0	1/0	0/0	0/0	(1)	1/0	1/0	4/4	1/0	3/0	0/0	1/1	1/1	1/1	0/0																	
Cobalt dichloride	CoCl <sub>2</sub>	007646-79-9	aqueous	Xn		1/1	1/1	(2)	(2)	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	1/0	1/0	1/0	0/0	(3)	0/0	0/0																		
Cocoa	—	—		(—)		1/1	1/1	(2)	(1)	(2)	0/0	1/1	(2)	1/1	0/0	0/0	0/0	0/0	1/1	1/1	(1)	(1)	(2)	(1)	(2)	0/0	(1)	(1)	(1)																		
Cocoa butter	—	008002-31-1		—		0/0	0/0	1/0	(1)	1/0	0/0	1/1	(2)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	1/1	(1)	4/4	1/0	4/4	0/0	(1)	1/1	1/1																		
Coconut butter	—	—		—		0/0	0/0	1/0	(2)	1/0	0/0	(2)	1/1	0/0	0/0	0/0	0/0	1/1	0/0	(1)	1/1	1/1	4/4	1/1	1/0	0/0	(1)	1/1	1/1																		
Coconut fatty alcohol	—	068425-37-6	techn. pure (Xi)	—		1/0	0/0	(1)	(2)	1/0	0/0	(2)	1/3	0/0	0/0	1/3	0/0	0/0	0/0	(1)	1/1	1/1	3/0	1/1	1/1	0/0	(1)	1/1	1/1																		
Coconut oil	—	008001-31-8	techn. pure	—		1/3	1/3	1/0	(2)	1/0	0/0	(2)	1/1	0/0	0/0	1/3	0/0	0/0	0/0	(1)	1/1	1/1	4/4	1/1	1/1	0/0	(1)	1/1	1/1																		
Cod-liver oil	—	008001-69-2		—		1/3	1/3	(2)	1/0	(2)	0/0	(2)	1/3	1/1	0/0	1/0	0/0	1/1	0/0	(1)	1/1	1/1	3/0	1/0	1/0	0/0	(1)	(1)	1/1																		
Colza oil	—	008002-13-9		—		0/0	0/0	(2)	(2)	1/0	0/0	(2)	1/3	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/0	1/3	0/0	(1)	1/1	1/1																		
Compressed air	—	—	oleagineus	—		1/0	0/0	(2)	(2)	(1)	0/0	(1)	3/0	0/0	0/0	3/0	0/0	0/0	0/0	(1)	1/1	1/1	(3)	(1)	(2)	0/0	1/1	1/1	1/1																		
Condy's crystals	-> see: Potassium permanganate																																														
Copper acetate	C <sub>4</sub> H <sub>8</sub> CuO <sub>4</sub>	004180-12-5	aqueous	Xn		1/1	1/1	(3)	(2)	(2)	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	1/0	(3)	3/3	0/0	4/4	1/1	1/1	1/1	verdigris																
Copper sulfate	CuSO <sub>4</sub> x 5H <sub>2</sub> O	007758-99-8	aqueous	Xn		1/1	1/1	1/0	1/0	(2)	1/0	1/0	1/1	1/1	1/0	1/3	1/0	1/1	1/1	(1)	1/1	1/1	1/0	1/1	2/0	0/0	4/4	1/1	1/1	1/1	blue stone																
Cotton oil	—	008001-29-4	techn. pure	?		0/0	0/0	1/0	(2)	(2)	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	3/0	1/0	1/0	0/0	(1)	1/1	1/1																		
Creosote	—	—		(T)		1/1	1/1	3/0	(3)	0/0	0/0	(3)	3/4	0/0	1/0	3/0	4/4	0/0	0/0	(1)	1/1	(3)	4/4	(3)	1/0	0/0	(2)	1/1	1/1	0/0																	
Creosote	-> see: Carbolineum																																														
Crezol (-mixtures)	C <sub>7</sub> H <sub>8</sub> O	001319-77-3		T, C		3/4	4/4	4/4	4/4	4/4	4/4	4/4	2/3	4/4	4/4	4/4	4/4	3/4	1/2	1/1	1/1	1/1	4/4	1/0	4/4	0/0	1/1	1/0	1/0	1/1																	
Crotonaldehyde	C <sub>6</sub> H <sub>8</sub> O	004170-30-3	techn. pure	F, T	X	1/0	0/0	(2)	(4)	0/0	(4)	(2)	1/0	0/0	0/0	4/4	0/0	0/0	0/0	(1)	1/0	1/3	1/0	3/0	4/4	0/0	1/0	1/1	1/1	0/0																	
Crude oil	—	—	100 %	(N)		0/0	1/3	1/0	(3)	1/0	0/0	1/0	1/3	3/0	1/0	1/0	3/0	0/0	0/0	(1)	1/1	1/1	4/4	1/0	3/3	0/0	(2)	(1)	(1)																		
Cumene	C <sub>9</sub> H <sub>12</sub>	000098-82-8		Xi	X	2/3	3/4	(2)	4/4	0/0	4/4	(2)	3/4	4/4	4/4	4/4	0/0	0/0	1/2	1/1	(1)	(2)	4/4	1/0	4/4	0/0	1/1	1/1	1/1	0/0																	
Cupric chloride	CuCl <sub>2</sub>	007447-39-4	saturated	Xn		1/3	1/1	(3)	1/0	(2)	1/0	(2)	1/3	0/0	0/0	1/1	1/0	0/0	0/0	(1)	1/1	1/1	1/0	1/1	1/0	0/0	4/4	4/4	4/4	1/1																	
Cupric nitrate	Cu(NO <sub>3</sub> ) <sub>2</sub>	003251-23-8	saturated	O, Xn		1/1	1/1	1/0	(2)	(2)	1/0	1/0	1/1	1/0	0/0	1/0	1/0	0/0	0/0	(1)	1/1	1/1	1/0	1/1	4/4	0/0	4/4	1/1	1/1	1/1																	
Cupric nitrate	Cu(NO <sub>3</sub> ) <sub>2</sub>	003251-23-8	aqueous	O, Xn		0/0	0/0	(3)	(2)	0/0	1/0	1/1	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/1	1/0	0/0	4/4	1/1	1/1	1/1																	
Cuprous chloride	CuCl	007758-89-6	aqueous	Xn		0/0	0/0	(3)	(2)	(2)	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/1	1/0	0/0	4/4	4/4	4/4	1/1																	
Cuprous cyanide	CCuN	000544-92-3	saturated	T		1/1	1/1	(2)	(2)	(2)	0/0	(1)	1/3	0/0	0/0	1/0	1/0	0/0	0/0	(1)	1/1	1/1	1/0	1/1	1/0	0/0	(3)	1/1	1/1																		
Curry	—	—		?		0/0	0/0	(2)	(2)	(2)	0/0	(1)	(2)	3/3	0/0	0/0	0/0	0/0	1/1	0/0	1/1	(1)	(2)	(2)	0/0	(1)	(1)		possibility of discoloration																		
Cyanoethylene	-> see: Acrylonitrile																																														
Cyanomethane	-> see: Acetonitrile																																														
Cyclanon	—	—		(Xn, Xi)		1/1	1/1	1/0	(2)	(1)	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	(1)	(2)	(2)	1/1	0/0	3/4	(1)	(1)	0/0	appliances for dyeing-mill; BASF																
Cyclohexane	C <sub>6</sub> H <sub>12</sub>	000110-82-7		F	X	3/4	3/4	1/0	3/3	1/0	4/4	1/1	3/4	4/4	4/4	2/3	1/0	1/3	1/2	1/1	1/1	1/1	4/4	1/0	1/0	0/0	1/1	1/1	1/1	0/0																	
Cyclohexanol	C <sub>6</sub> H <sub>12</sub> O	000108-93-0	techn. pure	Xn		1/1	1/1	1/1	3/0	0/0	1/2	1/0	1/3	3/3																																	



CHEMICALS	thermoplastics															fluoroplastics		elastomers		metals		COMMENT										
	FORMULA	CAS-NR.	CONCENTRATION	HAZARD NOTE	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HART	PVC WEICH	SAN	ECTFE / ETFE	PEP	PTFE		PVDF	EPDM	FKM / FKM	NBR	SI	AL	V2A	V4A	Haselloy C	
Desiccator fat	—	—	—	—	0/0	1/3	1/0	(2)	(1)	(0)	(1)	(0)	(0)	(0)	(0)	(0)	(0)	(0)	(1)	1/1	(1)	(3)	(2)	(2)	0/0	(1)	(1)	(1)				
Desmodur 44	C <sub>15</sub> H <sub>10</sub> N <sub>2</sub> O <sub>2</sub>	000101-68-8		Xn	0/0	0/0	0/0	(3)	0/0	0/0	(2)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	(2)	0/0	4/4	0/0	(1)	(1)	(1)				
Developer for fotos	—	—	—	?	1/3	1/1	4/4	(2)	1/0	0/0	1/3	1/2	0/0	1/0	1/3	1/0	0/0	0/0	(1)	1/1	1/1	3/0	1/0	1/0	0/0	1/1	1/0	1/0				
Developer liquids	—	—	—	?	1/1	1/1	4/4	1/0	1/0	0/0	1/0	1/1	0/0	1/0	1/1	1/0	0/0	0/0	0/0	1/1	(1)	2/0	1/0	3/3	0/0	1/1	1/0	1/0	0/0			
Dextrin	(C <sub>6</sub> H <sub>10</sub> O <sub>5</sub> ) <sub>n</sub> x H <sub>2</sub> O	009004-53-9	aqueous	—	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1		
Diacetone alcohol	C <sub>8</sub> H <sub>12</sub> O <sub>2</sub>	000123-42-2		Xi	X	0/0	0/0	(3)	(3)	0/0	0/0	1/0	2/2	0/0	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(2)	1/0	4/4	4/4	0/0	(2)	(1)	(1)			
Diamine	-> see: Hydrazine																															
Diaminoethane	C <sub>2</sub> H <sub>6</sub> N <sub>2</sub>	000107-15-3	techn. pure	C, Xn	X	1/1	1/3	1/0	(3)	0/0	1/0	1/0	1/1	0/0	0/0	3/0	4/4	0/0	0/0	(1)	1/1	1/4	1/0	4/4	3/3	0/0	1/1	(1)	(1)	0/0		
Diammonium sulfide	-> see: Ammonium sulfide																															
Diamyl phthalate	C <sub>18</sub> H <sub>26</sub> O <sub>4</sub>	000131-18-0	100 %	(T)		0/0	1/3	(1)	(4)	0/0	0/0	(2)	(2)	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	3/0	3/0	4/4	0/0	(1)	(1)	(1)	0/0		
Dibenzyl sebacate	C <sub>24</sub> H <sub>38</sub> O <sub>4</sub>	??		?		0/0	0/0	(2)	(3)	0/0	0/0	(2)	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	2/0	(4)	4/4	0/0	(1)	(1)	(1)		plasticiser	
Dibromoethane, 1,2-	-> see: Ethylene dibromiden (EDB)																															
Dibromotetrafluoroethane	C <sub>2</sub> Br <sub>2</sub> F <sub>4</sub>	000124-73-2		?		0/0	0/0	1/0	(3)	0/0	0/0	1/0	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	0/0	4/4	3/0	3/0	0/0	(3)	0/0	0/0				
Dibutyl phthalate, n-	C <sub>16</sub> H <sub>22</sub> O <sub>4</sub>	000084-74-2	FR, 80°C	T		0	0	0	0	0	0	0	0	0	0	0	0	0	0	(1)	0	0	0	4/4	0	0	0	0	0/0	plasticiser		
Dibutyl phthalate, n-	C <sub>16</sub> H <sub>22</sub> O <sub>4</sub>	000084-74-2		T		1/3	3/3	1/0	4/4	1/0	0/2	1/0	2/2	4/4	1/0	4/4	4/4	0/4	1/1	(1)	1/1	1/3	3/0	2/3	4/4	0/0	(1)	1/1	1/0	0/0	plasticiser	
Dibutyl sebacate	C <sub>18</sub> H <sub>34</sub> O <sub>4</sub>	000109-43-3	techn. pure	—		1/0	1/3	1/0	(3)	0/0	0/0	(2)	1/0	4/4	0/0	4/4	4/4	0/0	(1)	1/1	1/0	3/0	4/4	4/4	0/0	(1)	(1)	(1)	0/0	plasticiser		
Dibutylamine	C <sub>8</sub> H <sub>17</sub> N	000111-92-2		Xn	X	0/0	0/0	(2)	(3)	0/0	(3)	(2)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	4/4	4/4	0/0	(1)	(1)	(1)			
Dichloroacetic acid	C <sub>2</sub> H <sub>2</sub> Cl <sub>2</sub> O <sub>2</sub>	000079-43-6	50 %	C		1/1	1/1	4/4	(4)	4/4	0/0	4/4	1/1	0/0	0/0	1/3	0/0	0/0	(1)	1/1	1/1	4/4	4/4	4/4	0/0	(4)	0/0	0/0	1/1			
Dichloroacetic acid	C <sub>2</sub> H <sub>2</sub> Cl <sub>2</sub> O <sub>2</sub>	000079-43-6	techn. pure	C		1/3	3/3	4/4	(4)	4/4	0/0	4/4	1/3	0/0	0/0	1/3	0/0	0/0	(1)	1/1	1/1	4/4	4/4	4/4	0/0	(4)	0/0	0/0	1/1			
Dichlorobenzene, 1,2-	C <sub>6</sub> H <sub>4</sub> Cl <sub>2</sub>	000095-50-1		Xn		3/3	3/4	(1)	4/4	0/0	3/4	(2)	3/4	4/4	4/4	4/4	4/4	1/3	(1)	1/1	1/1	4/4	1/0	4/4	0/0	(1)	0/0	0/0				
Dichlorobenzene, 1,4-	C <sub>6</sub> H <sub>4</sub> Cl <sub>2</sub>	000106-46-7		Xn		2/3	3/4	1/0	4/4	0/0	2/3	(2)	3/4	4/4	4/4	4/4	0/0	0/0	1/3	(1)	1/0	1/1	4/4	1/0	4/4	0/0	(1)	0/0	0/0			
Dichlorodifluoromethane	CCl <sub>2</sub> F <sub>2</sub>	000075-71-8	techn. pure	N		4/4	3/4	1/0	4/4	0/0	0/0	1/0	4/4	4/4	1/0	2/0	4/4	3/3	0/0	3/3	1/0	3/4	3/0	3/0	3/3	0/0	(3)	0/0	0/0	0/0		
Dichlorodifluoromethane	CCl <sub>2</sub> F <sub>2</sub>	000075-71-8		N		4/4	3/4	1/0	4/4	0/0	0/0	1/0	4/4	4/4	1/0	2/0	4/4	3/3	0/0	3/3	1/0	3/4	3/0	3/0	3/3	0/0	(3)	0/0	0/0	0/0		
Dichloroethane	C <sub>2</sub> H <sub>4</sub> Cl <sub>2</sub>	—		F, T	X	3/3	2/4	3/0	4/4	4/4	1/0	3/4	4/4	4/4	4/4	4/4	4/4	1/1	1/1	1/1	1/1	4/4	3/0	4/4	0/0	1/3	1/1L	1/1L	?	isomer not indicated in the source		
Dichloroethylene	C <sub>2</sub> H <sub>2</sub> Cl <sub>2</sub>	—	techn. pure	F+, Xn	X	4/4	4/4	3/0	(4)	4/4	(4)	4/4	3/0	4/4	0/0	4/4	4/4	0/0	(1)	1/0	1/1	4/4	3/4	4/4	0/0	(3)	1/1L	1/1L	?	isomer not indicated in the source		
Dichlorofluoromethane	CHCl <sub>2</sub> F	000075-43-4	100 %	N		0/0	3/0	1/0	3/0	0/0	0/0	1/0	4/4	4/4	3/0	4/4	4/4	3/3	0/0	(3)	1/0	(3)	4/4	4/4	4/4	0/0	(3)	0/0	0/0			
Dichlorohexafluorocyclobutane	C <sub>4</sub> Cl <sub>2</sub> F <sub>6</sub>	000356-18-3		?		0/0	0/0	1/0	(3)	0/0	0/0	1/0	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	0/0	1/0	(3)	1/0	0/0	(3)	0/0	0/0				
Dichloroisopropyl ether	C <sub>6</sub> H <sub>12</sub> Cl <sub>2</sub> O	—		(Xn)		(4)	(4)	(2)	(3)	0/0	(4)	(3)	(3)	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(3)	4/4	4/4	4/4	0/0	(3)	0/0	0/0		isomer not indicated in the source		
Dichloropropane	C <sub>3</sub> H <sub>6</sub> Cl <sub>2</sub>	—	100 %	F, T/Xn	X	0/0	0/0	(3)	-4	(4)	(4)	(2)	4/4	4/4	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(2)	4/4	(3)	4/4	0/0	(3)	0/0	0/0	0/0	isomer not indicated in the source	
Dichlorotetrafluoroethane	C <sub>2</sub> Cl <sub>2</sub> F <sub>4</sub>	000076-14-2		?		0/0	0/0	1/0	(3)	0/0	0/0	1/0	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	0/0	1/0	3/0	1/0	0/0	(3)	0/0	0/0				
Dicyclohexyl phthalate	C <sub>26</sub> H <sub>36</sub> O <sub>4</sub>	000084-61-7	techn. pure	(Xn)		0/0	0/0	(1)	(3)	0/0	0/0	(2)	1/3	0/0	0/0	0/0	0/0	0/0	(1)	(1)	0/0	(3)	4/4	4/4	0/0	(1)	(1)	(1)		plasticiser		
Dicyclohexylamine (DCHA)	C <sub>12</sub> H <sub>23</sub> N	000101-83-7		C, Xn		0/0	0/0	(2)	(3)	0/0	0/0	(2)	(2)	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	4/4	4/4	0/0	(1)	(1)	(1)				
Diesel fuel	—	—		Xn, N		1/3	0/0	1/1	3/3	1/1	0/0	1/1	1/3	0/0	1/0	0/0	0/0	0/0	(1)	1/1	1/1	4/4	1/0	1/1	0/0	1/1	(1)	(1)	0/0			
Diesel fuel for heating	—	—		Xn		3/3	3/4	1/0	3/3	1/0	2/3	1/1	1/3	3/4	1/2	1/1	3/3	1/1	1/1	1/1	1/1	4/4	1/1	1/1	0/0	1/1	1/1	1/1	0/0			
Diesel oil	—	068334-30-5	100 %	(Xn)		1/3	1/4	1/1	3/3	1/1	0/0	1/1	1/3	3/4	0/0	1/3	3/3	1/1	0/0	(1)	1/1	1/1	4/4	1/1	1/1	0/0	1/1	(1)	(1)	0/0		
Diethanolamine (DEA)	C <sub>4</sub> H <sub>11</sub> NO <sub>2</sub>	000111-42-2	100 %	Xi		0/0	1/0	(2)	(3)	0/0	0/0	(2)	1/2	1/0	0/0	0/0	0/0	1/1	0/0	(1)	1/0	1/3	3/0	(3)	4/4	0/0	1/1	(1)	(1)	0/0		
Diethyl ethyl	C <sub>8</sub> H <sub>18</sub> O	000060-29-7	techn. pure	F+, Xn	X	3/4	4/4	1/1	4/4	1/0	4/4	1/2	4/4	4/4	4/4	4/4	1/2	1/1	1/1	1/4	4/4	4/4	4/4	0/0	1/1	1/1	1/1	1/1	0/0			
Diethyl ketone	-> see: Pentanone, 3-																															
Diethyl malonate	C <sub>7</sub> H <sub>12</sub> O <sub>4</sub>	000105-53-3		Xi		1/1	1/1	(2)	3/4	0/0	1/2	(2)	1/1	4/4	3/3	2/4	0/0	0/0	1/1	1/1	(1)	(3)	(2)	(4)	(3)	0/0	(1)	(1)				
Diethyl sebacate	C <sub>14</sub> H <sub>26</sub> O <sub>4</sub>	000110-40-7		Xi		0/0	0/0	(2)	(3)	0/0	0/0	(2)	(2)	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	2/0	3/0	4/4	0/0	(1)	(1)	(1)		plasticiser		
Diethyl succinate	C <sub>8</sub> H <sub>14</sub> O <sub>4</sub>	000123-25-1		—		0/0	0/0	(2)	(4)	0/0	0/0	(3)	(2)	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	(2)	4/4	4/4	0/0	(1)	(1)	(1)				
Diethylamine	C <sub>4</sub> H <sub>11</sub> N	000109-89-7	techn. pure	F, C, Xn	X	0/0	0/0	(2)	(3)	0/0	0/0	(2)	1/2	0/0	0/0	3/0	0/0	0/0	(1)	1/0	1/4	2/0	4/4	4/4	0/0	(1)	1/1	1/1	0/0			
Diethylbenzene	C <sub>10</sub> H <sub>14</sub>	000135-01-3		Xi		3/4	4/4	(1)	3/4	0/0	4/4	(2)	4/4	4/4	4/4	0/0	0/0	1/2	(1)	(1)	(2)											



CHEMICALS	FORMULA	CAS-NR.	CONCENTRATION	HAZARD NOTE	FLAMMABLE	thermoplastics																	fluoroplastics		elastomers		metals		COMMENT			
						HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HART	PVC WEICH	SAN	ECTFE / ETFE	PEP	PTFE	PVDF	EPDM	FKM / FKM	NBR	SI	AL	V2A		V4A	Haselloy C	
Dimethyl ether	C <sub>2</sub> H <sub>6</sub> O	000115-10-6	gas	F+	X	0/0	3/0	1/0	(3)	1/0	0/0	(2)	4/4	4/4	0/0	3/0	4/4	0/0	0/0	0/0	1/0	(3)	3/0	4/4	4/4	0/0	1/1	(1)	(1)	0/0		
Dimethyl formamide (DMF)	C <sub>2</sub> H <sub>5</sub> NO	000068-12-2		T, F	X	1/1	1/3	1/0	4/4	1/0	1/1	1/2	1/1	4/4	4/4	3/4	0/0	4/4	2/2	1/1	1/1	4/4	2/0	4/4	4/4	0/0	(1)	1/1	1/1	1/1		
Dimethyl ketone	-> see: Acetone																															
Dimethyl phthalate (DMP)	C <sub>10</sub> H <sub>10</sub> O <sub>4</sub>	000131-11-3	100 %	(Xn)		4/4	1/3	(2)	4/4	0/0	0/0	(2)	2/3	4/4	0/0	4/4	4/4	4/4	0/0	(1)	1/1	(2)	3/0	2/0	4/4	0/0	(1)	(1)	(1)	0/0	plasticiser	
Dimethyl sulfoxide (DMSO)	C <sub>2</sub> H <sub>6</sub> SO	000067-68-5		Xi		1/1	1/1	(2)	4/4	0/0	1/1	1/0	1/1	1/2	4/4	4/4	0/0	0/0	1/2	1/1	(1)	(3)	(3)	(3)	(4)	0/0	(1)	(1)	(1)			
Dimethylacetone	-> see: Pentanone, 3-																															
Dimethylamine	C <sub>2</sub> H <sub>7</sub> N	000124-40-3	techn. pure	F+, Xn	X	1/3	1/3	1/0	4/4	0/0	0/0	(2)	1/3	0/0	0/0	3/4	4/4	0/0	0/0	(1)	1/1	3/0	3/0	4/4	4/4	0/0	(1)	(1)	(1)	1/1		
Dimethylaniline	C <sub>8</sub> H <sub>9</sub> N	—		T		0/0	0/0	(3)	4/4	0/0	0/0	(2)	4/4	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	3/0	4/4	4/4	0/0	(1)	(1)	(1)	0/0	isomer not indicated in the source	
Dinitro ethylene glycol	C <sub>2</sub> H <sub>4</sub> (NO <sub>2</sub> ) <sub>2</sub>	000628-96-6	diluted	(E, T+)		0/0	0/0	(3)	(3)	0/0	0/0	(2)	(2)	0/0	0/0	4/4	4/4	0/0	0/0	(1)	(1)	(3)	1/0	1/0	4/4	0/0	0/0	(1)	(1)	0/0		
Dinonyl phthalate (DNP)	C <sub>28</sub> H <sub>42</sub> O <sub>4</sub>	000084-76-4	techn. pure	Xn		3/0	0/0	(2)	3/0	0/0	0/0	(2)	1/3	0/0	0/0	4/4	0/0	0/0	0/0	(1)	1/0	(2)	(3)	4/4	4/4	0/0	(1)	(1)	(1)		plasticiser	
Diocetyl adipate	C <sub>22</sub> H <sub>42</sub> O <sub>4</sub>	000103-23-1		?		0/0	0/0	(2)	(3)	0/0	0/0	(2)	4/4	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	(2)	(3)	(3)	4/4	0/0	(1)	(1)	(1)		plasticiser	
Diocetyl phthalate (DOP)	C <sub>24</sub> H <sub>38</sub> O <sub>4</sub>	000117-81-7	techn. pure	Xn		4/4	4/4	1/0	4/4	1/0	1/0	(2)	4/4	4/4	1/0	4/4	4/4	0/0	0/0	1/1	1/0	(2)	3/0	2/3	4/4	0/0	(1)	(1)	(1)		plasticiser	
Diocetyl sebacate	C <sub>28</sub> H <sub>50</sub> O <sub>4</sub>	002432-87-3		—		0/0	0/0	(2)	(3)	0/0	0/0	(2)	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	2/0	3/0	4/4	0/0	(1)	(1)	(1)		plasticiser	
Dioxane	C <sub>8</sub> H <sub>16</sub> O <sub>2</sub>	000123-91-1		F, Xn	X	2/2	2/3	1/0	4/4	1/0	2/3	1/2	3/3	4/4	2/3	3/4	4/4	4/4	1/3	1/1	1/1	3/3	2/0	4/4	4/4	0/0	1/1	1/0	1/0	0/0		
Diphenyl ether	C <sub>12</sub> H <sub>10</sub> O	000101-84-8		Xn/Xi		0/0	1/0	3/0	(3)	(4)	0/0	1/1	4/4	4/4	0/0	0/0	4/4	4/4	0/0	(1)	1/0	(2)	4/4	3/0	4/4	0/0	(1)	(1)	(1)	0/0		
Diphenylamine	C <sub>12</sub> H <sub>11</sub> N	000122-39-4		T		0/0	0/0	0/0	(3)	0/0	0/0	(2)	(3)	0/0	0/0	0/0	4/4	0/0	0/0	(1)	(1)	(2)	(3)	(3)	(4)	0/0	(1)	(1)	(1)	0/0		
Diphenyl	—	008004-13-5		?		0/0	0/0	1/1	(3)	4/4	0/0	1/1	4/4	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	3/0	4/4	0/0	(1)	(1)	(1)		mixture with diphenyl and diphenyl ether; Bayer	
Dipropyl ketone	C <sub>9</sub> H <sub>18</sub> O	000123-19-3		—	X	0/0	0/0	(3)	(4)	(4)	(4)	1/0	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	(3)	(4)	4/4	0/0	(1)	(1)	(1)			
Dipropylene glycol	C <sub>8</sub> H <sub>16</sub> O <sub>3</sub>	025265-71-8		Xi		1/1	1/1	(2)	2/3	0/0	1/1	1/0	1/1	1/1	2/2	2/3	0/0	0/0	1/1	1/1	(1)	(2)	4/4	3/0	3/3	0/0	(1)	(1)	(1)			
Dipropylene glycol (mono)methyl ether	C <sub>8</sub> H <sub>16</sub> O <sub>2</sub>	—		—	X	0/0	0/0	(3)	(3)	0/0	0/0	(2)	(2)	0/0	0/0	0/0	4/4	0/0	0/0	(1)	(1)	(2)	(3)	(3)	4/4	0/0	(1)	(1)	(1)	0/0	isomer not indicated in the source	
Disodium phosphate	Na <sub>2</sub> HPO <sub>4</sub>	007558-79-4		(Xi)		1/1	1/1	1/0	(2)	1/0	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/0	(1)	0/0	(1)	1/1	1/1	0/0		
Dispersion of rubber	—	—		?		0/0	0/0	1/0	(2)	(2)	0/0	2/3	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(1)	(3)	(1)	(2)	0/0	(3)	(1)	(1)		latex	
Dithionous acid, disodium salt	-> see: Sodium hydrosulfite																															
Divinylene oxide	-> see: Furan																															
Dope, viscous ~	—	—		(Xn, Xi)		1/1	1/1	4/4	(3)	0/0	0/0		1/1	0/0	0/0	1/1	1/1	0/0	0/0	(1)	1/1	1/1	(3)	(2)	4/4	0/0	(3)	3/4	2/4	0/0		
Emulsifiers	—	—		?		0/0	0/0	(2)	0/0	0/0	0/0	0/0	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(1)	(2)	(2)	(3)	0/0	0/0	K	K			
Emulsions for fotos	—	—		?		1/0	0/0	1/0	(2)	(2)	0/0	1/0	1/1	0/0	0/0	1/0	0/0	0/0	0/0	(1)	1/1	1/1	(2)	(2)	(1)	0/0	(2)	0/0	0/0			
Ephetin	—	—	10% in water	?		0/0	0/0	0/0	0/0	0/0	0/0	1/1	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0		
Epichlorhydrin	C <sub>2</sub> H <sub>5</sub> ClO	000106-89-8	100 %	F, T	X	1/0	1/0	4/4	(4)	0/0	(4)	1/0	2/2	0/0	0/0	4/4	4/4	0/0	0/0	(1)	1/0	(3)	3/0	4/4	4/4	0/0	(3)	0/0	0/0	0/0		
Epoxypropane, 1,2-	-> see: Propylene oxid																															
Ethanal	-> see: Acetaldehyde																															
Ethanedioic acid	-> see: Oxalic acid																															
Ethanenitrile	-> see: Acetonitrile																															
Ethanoyl chloride	-> see: Acetyl chloride																															
Ethoxybenzene	C <sub>8</sub> H <sub>10</sub> O	000103-73-1		?		0/0	0/0	(2)	(4)	0/0	(3)	(2)	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	4/4	4/4	0/0	(1)	(1)	(1)		Ethyl phenyl ether; Phenyl ethyl ether; Phenetole	
Ethyl acetate	C <sub>4</sub> H <sub>8</sub> O <sub>2</sub>	000141-78-6	100 %	F	X	1/3	3/4	1/0	4/4	4/4	4/4	1/1	1/3	4/4	4/4	4/4	4/4	4/4	1/2	1/1	1/1	3/3	3/0	4/4	4/4	0/0	1/1	(1)	(1)	1/0		
Ethyl acrylate	C <sub>8</sub> H <sub>10</sub> O <sub>2</sub>	000140-88-5	100 %	F, Xn	X	4/4	4/4	1/0	(4)	(4)	(4)	(2)	4/4	0/0	0/0	4/4	4/4	0/0	0/0	1/1	1/0	3/0	4/4	4/4	4/4	0/0	(1)	(1)	(1)	1/0		
Ethyl alcohol	C <sub>2</sub> H <sub>6</sub> O	000064-17-5	40 %	—	X	1/1	1/2	1/0	1/2	1/1	1/2	1/2	1/1	2/3	1/2	1/1	0/0	1/1	1/1	1/1	1/1	1/1	1/0	1/0	1/1	0/0	1/1	1/1	1/1	1/1		
Ethyl alcohol	C <sub>2</sub> H <sub>6</sub> O	000064-17-5	50 %	—	X	1/1	1/1	1/0	1/1	1/1	1/0	1/2	1/1	1/0	1/0	1/0	3/0	0/0	0/0	1/1	1/1	1/1	1/0	(2)	1/1	0/0	1/1	1/1	1/1	1/1		
Ethyl alcohol	C <sub>2</sub> H <sub>6</sub> O	000064-17-5	96 %	F	X	1/0	1/3	1/0	1/3	1/1	1/2	1/2	1/1	3/4	1/2	1/3	3/0	1/3	1/1	1/1	1/1	1/1	1/0	3/0	3/3	0/0	1/1	1/1	1/1	1/1		
Ethyl aldehyde	-> see: Acetaldehyde																															
Ethyl benzoate	C <sub>9</sub> H <sub>10</sub> O <sub>2</sub>	000093-89-0		Xn		2/2	3/3	(2)	4/4	0/0	2/3	(2)	2/3	4/4	4/4	4/4	0/0	4/4	1/2	1/1	1/0	(3)	(3)	(3)	4/4	0/0	(1)	(1)	(1)			
Ethyl butyrate	C <sub>8</sub> H <sub>16</sub> O <sub>2</sub>	000105-54-4		F	X	2/3	2/4	(2)	4/4	0/0	3/4	(2)	2/4	4/4	4/4	4/4	0/0	0/0	1/2	1/1	(1)	(2)	(3)	(4)	4/4	0/0	(1)	(1)	(1)			
Ethyl chloride	-> see: Monochloroethane																															
Ethyl chloroacetate	C <sub>4</sub> H <sub>7</sub> ClO <sub>2</sub>	000105-39-5	techn. pure	T/Xi		1/1	1/1	(3)	4/4	(4)	(4)	(3)	1/1	4/4	0/0	3/4	3/4	0/0	0/0	(1)	1/1	1/4	3/0	4/4	4/4	0/0	3/4	0/0	0/0	0/0		
Ethyl cyanoacetate	C <sub>5</sub> H <sub>7</sub> NO <sub>2</sub>	000105-56-6		Xn/Xi		1/1	1/1	0/0	3/4	0/0	1/1	(2)	1/1	2/4	3/3	3/																

CHEMICALS	FORMULA	CAS-NR.	CONCENTRATION	HAZARD NOTE	FLAMMABLE	thermoplastics														fluoroelastomers		elastomers		metals		COMMENT						
						HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HART	PVC WEICH	SAN	ECTFE / ETFE	PEP	PTFE	PVDF	EPDM	FPM / FKM	NBR		SI	AL	V2A	V4A	Haselloy C	
Ethylene dibromiden (EDB)	C <sub>2</sub> H <sub>4</sub> Br <sub>2</sub>	000106-93-4		T		(4)	(4)	(2)	(4)	(4)	(4)	(2)	4/4	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	1/2	4/4	(3)	4/4	0/0	(3)	1/0L	1/0L	0/0	Dibromoethane, 1,2-;	
Ethylene glycol	C <sub>2</sub> H <sub>4</sub> O <sub>2</sub>	000107-21-1		Xn		1/1	1/1	3/3	2/3	1/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/0	1/2	1/1	0/0	1/1	1/1	1/1	1/1		
Ethylene glycol monobutyl ether	C <sub>8</sub> H <sub>16</sub> O <sub>2</sub>	000111-76-2	100 %	Xn	X	0/0	1/0	1/0	(2)	1/0	0/0	1/0	1/0	0/0	0/0	4/4	4/4	0/0	0/0	1/1	1/0	1/1	3/0	3/4	3/4	0/0	1/1	(1)	(1)	0/0		
Ethylene glycol monoethyl ether	C <sub>4</sub> H <sub>10</sub> O <sub>2</sub>	000110-80-5	100 %	T	X	0/0	4/4	(3)	(2)	0/0	0/0	1/0	2/4	4/4	1/0	4/4	4/4	4/4	0/0	1/1	1/0	1/1	3/0	4/4	4/4	0/0	(1)	(1)	(1)	0/0		
Ethylene glycol monoethyl ether acetate	C <sub>8</sub> H <sub>16</sub> O <sub>3</sub>	000115-15-9		Xn	X	1/1	1/2	0/0	3/4	0/0	1/2	(2)	1/2	4/4	4/4	3/4	0/0	0/0	1/2	1/1	(1)	(2)	2/0	4/4	4/4	0/0	(1)	(1)	(1)			
Ethylene glycol monomethyl ether	C <sub>3</sub> H <sub>8</sub> O <sub>2</sub>	000109-86-4	100 %	T	X	1/0	1/1	1/0	3/4	0/0	1/1	1/0	1/1	4/4	3/3	3/4	4/4	0/0	1/1	1/1	1/1	1/1	3/0	4/4	4/4	0/0	(1)	(1)	(1)	0/0		
Ethylene glycol monomethyl ether oleate	C <sub>22</sub> H <sub>40</sub> O <sub>3</sub>	000111-10-4		?		1/1	1/2	(2)	3/4	(2)	1/2	(2)	1/2	4/4	4/4	4/4	0/0	0/0	1/1	1/1	(1)	1/1	(1)	4/4	(2)	4/4	0/0	(1)	(1)	(1)	Kapsolat; Methoxyethyl oleate; Methyl cellosolveat oleate; plasticiser	
Ethylene oxide	C <sub>2</sub> H <sub>4</sub> O	000075-21-8		F+, T	X	2/3	3/3	3/0	3/4	1/0	3/4	1/0	3/3	4/4	1/1	3/4	0/0	0/0	1/1	1/1	(1)	1/1	4/4	4/4	4/4	0/0	1/1	(1)	(1)	0/0		
Ethylenediaminetetraacetic acid (EDTA)	C <sub>10</sub> H <sub>16</sub> N <sub>2</sub> O <sub>8</sub>	000060-00-4		Xi		1/1	1/1	(2)	(2)	(2)	0/0	1/0	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	(1)	(1)	(2)	(1)	0/0	(3)	0/0	0/0	0/0		
Ethylhexanol-1	C <sub>8</sub> H <sub>18</sub> O	000104-76-7		Xn/Xi		0/0	1/3	(2)	(2)	(1)	1/0	1/0	1/0	3/0	0/0	1/0	4/4	0/0	0/0	(1)	1/1	(1)	1/0	1/0	1/0	0/0	(1)	(1)	(1)	1/1		
Ethyne	-> see: Acetylene																															
Eucalyptus oil		008000-48-8		?		0/0	0/0	(2)	(3)	0/0	0/0	(2)	(2)	4/4	0/0	0/0	0/0	3/3	0/0	(1)	(1)	(2)	4/4	(3)	(4)	0/0	(1)	(1)	(1)			
Exhaust gases, alkaline				?		1/1	0/0	(2)	0/0	0/0	0/0	(1)	1/1	0/0	0/0	1/1	0/0	0/0	0/0	0/0	1/1	1/4	1/0	1/0	1/0	0/0	(2)	(1)	(1)			
Exhaust gases, containing carbon dioxide			small	?		1/1	0/0	(1)	(1)	(1)	(1)	(1)	1/1	(1)	(1)	1/1	(1)	1/1	1/1	1/1	1/1	1/1	1/0	1/0	(1)	(1)	(1)	(1)	(1)	0/0		
Exhaust gases, containing hydrochloric acid			each	?		1/1	0/0	(3)	0/0	0/0	0/0	(4)	1/1	0/0	0/0	1/1	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/0	3/0	0/0	(4)	2/2L	2/2L	3/3		
Exhaust gases, containing hydrogen fluoride			small	?		1/1	0/0	(3)	0/0	0/0	(4)	1/1	0/0	0/0	(1)	0/0	0/0	(2)	1/1	1/1	1/1	1/0	1/0	1/0	0/0	(4)	(2)	(2)	1/1			
Exhaust gases, containing nitrose			small	?		1/1	0/0	(3)	0/0	0/0	(4)	1/3	0/0	0/0	1/1	0/0	0/0	(2)	1/1	1/1	1/1	1/0	1/0	(3)	0/0	(2)	(1)	(1)				
Exhaust gases, containing sulfur dioxide			small	?		1/1	0/0	(2)	0/0	0/0	(4)	1/1	0/0	0/0	1/1	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/0	3/0	0/0	(4)	1/1	1/1	0/0			
Exhaust gases, containing sulfur trioxide			small	?		1/1	0/0	(4)	0/0	0/0	(4)	4/4	0/0	0/0	1/1	0/0	0/0	(2)	(2)	1/1	1/1	1/0	1/0	4/4	0/0	(4)	(2)	(1)	0/0			
Exhaust gases, containing sulfuric acid			each	?		1/1	0/0	(4)	0/0	0/0	(4)	1/3	0/0	0/0	1/1	0/0	0/0	(2)	1/1	1/1	1/1	1/0	1/0	4/4	0/0	(4)	(2)	(1)	0/0			
Fat, animal						0/0	0/0	1/0	(2)	1/0	0/0	1/1	1/3	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	4/4	1/0	1/0	0/0	(1)	1/1	1/1			
Fat, mineral				(-)		0/0	0/0	1/0	(2)	(1)	0/0	1/1	1/3	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	(4)	(1)	1/0	0/0	(1)	1/1	1/1			
Fat, vegetable						0/0	0/0	1/0	(2)	1/0	0/0	1/1	1/3	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	4/4	1/0	1/0	0/0	(1)	1/1	1/1				
Fats, edible oil						0/0	1/0	1/0	1/0	1/0	1/0	1/1	3/0	0/0	1/0	1/0	3/0	0/0	0/0	(1)	1/1	1/1	4/4	1/0	1/1	0/0	(1)	1/1	1/1	1/1		
Fatty alcohol sulfonates			aqueous	(Xn, Xi)		1/1	0/0	1/0	(2)	1/0	0/0	1/1	3/0	0/0	1/1	0/0	0/0	1/3	0/0	0/0	(1)	1/1	1/1	(2)	(2)	1/1	0/0	3/4	1/0	1/0	0/0	detergents
Ferric chloride	FeCl <sub>3</sub>	007705-08-0	saturated	Xn		1/1	1/1	3/0	1/0	0/0	1/0	4/4	1/1	1/1	1/0	1/1	1/0	1/1	1/1	1/1	1/1	1/1	(1)	1/1	1/1	0/0	4/4	4/4	4/4	1/1		
Ferric nitrate	Fe(NO <sub>3</sub> ) <sub>3</sub>	010421-48-4	aqueous	(O, Xn)		1/1	1/1	(2)	(2)	0/0	0/0	(3)	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	(1)	1/0	0/0	4/4	1/1	1/1	1/1			
Ferric nitrate	Fe(NO <sub>3</sub> ) <sub>3</sub>	010421-48-4	aqueous	O, Xn		1/1	1/1	1/0	0/0	1/0	(3)	1/1	1/1	0/0	1/1	1/0	1/1	1/1	1/1	1/1	1/1	(1)	1/0	0/0	4/4	1/1	1/1	1/1				
Ferric sulfate	Fe <sub>2</sub> (SO <sub>4</sub> ) <sub>3</sub>	010028-22-5	saturated	Xi		1/1	1/1	(2)	(2)	0/0	0/0	(3)	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	(1)	(1)	(1)	0/0	4/4	1/1	1/1	1/1		
Ferrous chloride	FeCl <sub>2</sub>	007758-94-3	saturated	Xn		1/1	1/1	3/0	1/0	(2)	1/0	(3)	1/1	1/1	1/0	1/1	1/0	1/1	1/1	1/1	1/1	1/1	(1)	1/1	1/1	0/0	4/4	(2)	1/1	1/1		
Ferrous sulfate	FeSO <sub>4</sub>	007720-78-7	saturated	(Xn)		1/1	1/1	(2)	1/0	1/0	(3)	1/1	1/0	0/0	1/1	1/0	0/0	1/1	1/1	1/1	1/1	(1)	(1)	1/0	0/0	4/4	1/1	1/1	1/1			
Ferrous sulfate	FeSO <sub>4</sub>	007720-78-7	aqueous	(Xn)		1/1	1/1	(2)	(2)	0/0	0/0	(3)	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	(1)	(1)	1/0	0/0	4/4	1/1	1/1	1/1		
Ferrous sulfate	FeSO <sub>4</sub>	007720-78-7		Xn		1/1	1/1	(2)	1/0	(2)	0/0	(3)	1/1	1/1	0/0	0/0	0/0	1/1	1/1	1/1	1/1	(1)	1/0	(1)	0/0	4/4	1/1	1/1	1/1			
Fire-damp				F+	X	0/0	0/0	1/0	(2)	(1)	0/0	(1)	(2)	0/0	0/0	0/0	0/0	0/0	(1)	1/1	(1)	4/4	1/0	1/0	0/0	1/1	(1)	(1)		mainly methane		
Fixer for fotos				?		1/0	1/1	1/0	(2)	0/0	0/0	1/0	1/1	0/0	0/0	1/3	1/0	0/0	0/0	(1)	1/1	1/1	1/0	1/0	0/0	(2)	1/0	1/0				
Fluid 101, 100°C				?		0	0	0	0	0	0	(3)	0	0	0	0	0	0	0	0	0	0	0	0	0	3	0	0	0	0	Brake fluid, based on polyglycoles	
Fluorides				T		1/1	1/1	(2)	1/1	(2)	1/1	(1)	1/1	2/2	1/1	0/0	0/0	1/1	1/1	(1)	(1)	(2)	(2)	(1)	0/0	0/0	K	K				
Fluorine	F <sub>2</sub>	007782-41-4		O, T+, C+		4/4	4/4	4/4	4/4	4/4	3/4	4/4	4/4	4/4	4/4	1/2	0/0	4/4	1/1	1/1	1/1	4/4	4/4	3/0	4/4	0/0	4/4	(4)	(4)	0/0		
Fluorobenzene	C <sub>6</sub> H <sub>5</sub> F	000462-06-6		F, (Xn)	X	0/0	0/0	(2)	(4)	0/0	(4)	(2)	(3)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(2)	4/4	3/0	4/4	0/0	(1)	0/0	0/0			
Fluorocarbons				?		0/0	0/4	(2)	(3)	(2)	0/0	(3)	4/4	0/0	0/0	0/0	0/4	1/1	0/0	0/1	(3)	(3)	(3)	(3)	0/0	(1)	0/0	0/0		resistance depends on type		
Formaldehyde solution	CH <sub>2</sub> O	000050-00-0	10 %	Xn		1/1	1/1	3/3	1/2	1/0	1/2	1/2	1/1	3/4	2/3	2/3	3/3	1/3	1/1	1/1	1/1	1/1	1/0	3/0	(2)	0/0	1/1	1/1	1/1	1/1		
Formaldehyde solution	CH <sub>2</sub> O	000050-00-0	30 %	T		1/1	1/1	3/3	1/2	1/0	0/0	1/2	1/1	4/4	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	3/0	1/0	0/0	1/1	1/1	1/1	1/1			
Formaldehyde solution	CH <sub>2</sub> O	000050-00-0	40 %	T		1/2	2/3	1/3	1/2	1/0	1/2	1/2	1/2	4/4	2/3	2/3	3/3	0/4	1/1	1/1	1/1	1/1	1/0	3/0	(3)	0/0	1/1	1/1	1/1			
Formamide	CH <sub>3</sub> NO	000075-12-7																														



CHEMICALS	FORMULA	CAS-NR.	CONCENTRATION	HAZARD NOTE	thermoplastics													fluoroplastics		elastomers		metals		COMMENT							
					FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HART	PVC WEICH	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM		FKM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C
Gas oil	—	—	—	(Xn)	0/0	0/0	(1)	(2)	1/0	0/0	(2)	1/3	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	4/4	1/0	1/0	0/0	1/1	(1)	(1)			
Gas, natural	—	—	—	F+	X	0/0	0/0	0/1	0/0	1/0	0/0	1/0	(2)	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(1)	4/4	1/0	1/0	0/0	1/1	(1)	(1)	mainly methane		
Gasoline	—	008006-61-9	—	(F, Xn)	X	0/0	0/0	(1)	3/4	(2)	0/0	1/2	3/4	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	4/4	1/0	3/0	0/0	1/1	(1)	(1)			
Gasoline	C <sub>8</sub> H <sub>12</sub> · C <sub>12</sub> H <sub>26</sub>	086290-81-5	—	F, Xn, N	X	2/3	3/4	1/0	3/3	(2)	2/3	1/2	3/4	4/4	3/3	2/4	0/0	0/4	1/1	1/1	1/1	4/4	(1-3)	3/0	0/0	1/1	1/1	1/1	fuel, lead-free		
Gearbox oil, EP (Hypoid), 110°C	—	—	—	?		0	0	1	1	1	0	4	(3)	0	0	0	0	0	0	(2)	0	4/4	0	4/4	0	(1)	1	1	0/0		
Gelatin	—	009000-70-8	each	—	—	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/0	1/0	0/0	1/1	1/1	1/1	1/1	1/1	1/1	0/0	1/1	1/1	1/1	0/0		
Genantin	—	—	—	Xn	—	0/0	0/0	3/3	(2)	1/0	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/0	1/2	1/1	0/0	1/1	1/1	1/1	antifreeze agent , based on glycol; Clariant		
Ginger	—	—	ground	?	—	0/0	0/0	(2)	(2)	(2)	0/0	(1)	(2)	4/4	0/0	0/0	0/0	3/3	0/0	(1)	(1)	(1)	(2)	(1)	(2)	0/0	(1)	(1)	(1)		
Glucose	C <sub>6</sub> H <sub>12</sub> O <sub>6</sub>	000050-99-7	each	—	—	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1		
Glue (bone glue)	—	—	each	—	—	1/0	1/1	(1)	(1)	1/1	0/0	(2)	1/1	0/0	0/0	1/3	0/0	0/0	0/0	0/0	1/1	1/1	1/0	1/0	0/0	(3)	1/1	1/1	0/0		
Glycerol	C <sub>3</sub> H <sub>8</sub> O <sub>3</sub>	000056-81-5	each	Xi	—	1/1	1/1	1/0	3/3	1/0	1/1	1/0	1/1	1/1	1/1	1/1	2/3	1/1	1/1	1/1	1/1	1/1	1/0	1/1	1/0	0/0	1/1	1/1	1/1	Glycerin; Propanetriol, 1,2,3-; Trihydroxypropane, 1,2,3-	
Glycine	C <sub>2</sub> H <sub>5</sub> NO <sub>2</sub>	000056-40-6	10 %	—	—	1/1	1/1	1/1	1/1	(1)	0/0	1/1	1/1	0/0	0/0	1/3	1/3	0/0	1/1	1/1	1/1	1/1	1/0	3/3	0/0	(2)	(2)	0/0	Glyccol; Aminoacetic acid		
Glycolic acid	C <sub>2</sub> H <sub>4</sub> O <sub>3</sub>	000079-14-1	37 %	Xn	—	1/1	0/0	4/4	(2)	0/0	(3)	1/1	0/0	0/0	(3)	1/1	0/0	0/0	0/0	0/0	1/1	1/3	1/0	2/0	1/0	0/0	1/0	1/3	1/1		
Glycolic acid	C <sub>2</sub> H <sub>4</sub> O <sub>3</sub>	000079-14-1	70 %	C, Xn	—	1/1	1/1	4/4	(2)	0/0	(3)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(2)	1/0	3/0	(2)	0/0	(2)	1/3	1/3	1/1		
Glysantin	—	—	—	Xn	—	1/1	1/1	3/3	(2)	1/0	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/2	1/1	0/0	1/1	1/1	1/1	antifreeze agent , based on glycol; BASF	
Gum tragacanth	—	009000-65-1	—	—	—	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1		
HD-Oil motor oil, without aromatics	—	—	—	?	—	1/0	1/3	1/0	1/1	1/1	0/0	1/1	1/3	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	(2)	4/4	(1)	3/3	0/0	1/1	1/1	1/1		
Helium	He	007440-59-7	—	—	—	0/0	0/0	1/0	(1)	1/1	0/0	1/1	1/0	0/0	0/0	0/0	0/0	0/0	0/0	1/1	(1)	1/1	(1)	1/0	1/0	1/0	0/0	1/1	1/1		
Henkel-P3-solution	—	—	—	?	—	1/1	1/1	(2)	(2)	(1)	0/0	(1)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	(1)	(2)	(2)	1/0	0/0	0/0	1/1	1/1	cleaner	
Heptane, normal	C <sub>7</sub> H <sub>16</sub>	000142-82-5	—	F, Xn	X	2/3	3/4	1/0	1/2	1/0	3/3	1/2	2/4	4/4	1/2	2/3	4/4	1/0	1/1	1/1	1/1	1/1	4/4	1/1	1/1	0/0	1/1	1/1	1/1	0/0	
Heptanol, 1-	C <sub>7</sub> H <sub>16</sub> O	000111-70-6	—	Xn	—	0/0	0/0	(2)	(2)	(1)	0/0	(1)	(2)	0/0	0/0	0/0	0/0	1/3	0/0	(1)	(1)	4/4	(1)	1/0	0/0	(1)	(1)	(1)	(1)		
Heptanone	C <sub>7</sub> H <sub>14</sub> O	—	—	(Xn)	X	0/0	0/0	(3)	(4)	(4)	(2)	(3)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	(4)	(4)	4/4	0/0	(1)	(1)	(1)	isomer not indicated in the source	
Hexachlorbenzene (HCB)	C <sub>6</sub> Cl <sub>6</sub>	000118-74-1	—	T	—	0/0	0/0	(3)	(4)	0/0	(4)	1/0	(3)	0/0	0/0	0/0	0/0	1/1	0/0	(1)	(2)	0/0	4/4	(3)	4/4	0/0	(1)	0/0	0/0		
Hexachlorcyclohexane (alpha-BHC)	C <sub>6</sub> HCl <sub>6</sub>	000319-84-6	—	T	—	0/0	0/0	(3)	(4)	0/0	(3)	(3)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(2)	0/0	4/4	1/0	4/4	0/0	(3)	0/0	0/0		
Hexahydropyridine	—	—	—	—	—	-> see: Piperidine																									
Hexaldehyde, n-	C <sub>6</sub> H <sub>12</sub> O	000066-25-1	—	F, Xi	X	0/0	0/0	0/0	(4)	0/0	0/0	(2)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	3/0	4/4	4/4	0/0	(1)	(1)	(1)		
Hexamethylenetetramine	C <sub>6</sub> H <sub>12</sub> N <sub>4</sub>	000100-97-0	—	F, Xn	X	0/0	0/0	(2)	(2)	1/0	0/0	(2)	(2)	1/1	0/0	0/0	0/0	1/1	0/0	(1)	(1)	(2)	(2)	(2)	(3)	0/0	(1)	1/1	1/1	0/0	Methenamine; Hexamine; Urotropin
Hexane, n-	C <sub>6</sub> H <sub>14</sub>	000110-54-3	—	F, Xn	X	2/3	4/4	1/0	(2)	1/0	3/4	1/1	2/3	4/4	1/2	2/4	4/4	1/1	1/1	1/1	1/1	4/4	1/1	1/1	0/0	1/1	1/1	1/1	0/0		
Hexanedioic acid	—	—	—	—	—	-> see: Adipic acid																									
Hexanetriol	C <sub>6</sub> H <sub>14</sub> O <sub>3</sub>	—	100 %	?	—	1/1	1/1	(2)	(2)	(1)	0/0	(1)	1/1	1/0	0/0	1/1	3/3	1/1	0/0	(1)	1/1	(1)	1/0	1/0	1/0	0/0	(1)	(1)	(1)	0/0	isomer not indicated in the source
Hexene, 1-	C <sub>6</sub> H <sub>12</sub>	000592-41-6	—	F, Xn	X	0/0	0/0	1/0	(2)	(1)	(4)	(1)	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(1)	4/4	1/0	3/3	0/0	1/1	1/1	1/1	Butyl ethylene; Hexylene	
Hexyl alcohol	C <sub>6</sub> H <sub>14</sub> O	000111-27-3	—	Xn	—	1/0	1/0	(2)	(2)	(1)	0/0	(1)	1/2	0/0	3/0	1/0	3/0	1/3	0/0	(1)	1/0	(1)	4/4	1/0	1/0	0/0	(1)	(1)	(1)	0/0	
Honey	—	—	—	—	—	1/1	1/1	1/1	1/1	1/1	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/1	0/0	(1)	(1)	(1)	0/0	
Hydraulic fluids, HFA	—	—	50°C	?	—	0	0	0	0	0	0	0	(3)	0	0	0	0	0	0	0	(1)	0	4	0	1	0	(2)	0	0		
Hydraulic fluids, HFB	—	—	50°C	?	—	0	0	0	0	0	0	0	(3)	0	0	0	0	0	0	0	(1)	0	4	0	1	0	(2)	0	0		
Hydraulic fluids, HFC	—	—	60°C	?	—	0	0	0	0	0	0	0	(3)	0	0	0	0	0	0	0	(1)	0	0	0	1	0	(2)	0	0		
Hydraulic fluids, HFD-R	—	—	100°C	?	—	0	0	0	0	0	0	0	(3)	0	0	0	0	0	0	0	0	0	0	0	4	0	(2)	0	0		
Hydraulic fluids, HFD-S	—	—	100°C	?	—	0	0	0	0	0	0	0	(3)	0	0	0	0	0	0	0	0	0	0	0	4	0	(2)	0	0		
Hydraulic oil (based on mineral oil)	—	—	—	?	—	0/0	0/0	0/0	0/0	(1)	0/0	1/0	1/3	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	0/0	4/4	(1)	1/0	0/0	1/1	1/1	1/1		
Hydrazine	N <sub>2</sub> H <sub>4</sub>	000302-01-2	10 %	T	X	1/1	1/0	4/4	(4)	0/0	0/0	2/0	1/1	0/0	0/0	1/0	0/0	0/0	0/0	1/0	1/0	1/3	1/0	3/4	4/4	0/0	1/0	1/3	1/3	1/1	Diamide; Diamine; Nitrogen hydride
Hydrazine hydrate	N <sub>2</sub> H <sub>4</sub> O	010217-52-4	aqueous	(T, C)	(X)	1/1	1/0	4/4	(4)	0/0	0/0	2/0	1/1	0/0	0/0	1/0	0/0	0/0	0/0	1/0	1/0	1/3	1/0	3/4	4/4	0/0	1/0	1/3	1/3	0/0	
Hydrocyanic acid, sodium salt	—	—	—	—	—	-> see: Sodium cyanide																									
Hydrogen	H <sub>2</sub>	001333-74-0	techn. pure	F+	X	1/1	1/1	1/0	1/0	0/0	0/0		1/1	1/0	0/0	1/1	1/1	0/0	0/0	(1)	1/1	1/1	1/0	1/0	1/1	0/0	1/1	1/1	1/1	1/1	
Hydrogen bromide	HBr	010035-10-6	40 %	C	—	1/0	1/1	4/4	4/4	(4)	4/4	4/4	1/1	4/4	0/0	1/1	3/3	0/0	0/0	1/1	1/1	1/1	3/0	1/0	4/4	0/0	(4)	(4)	(4)	0/0	
Hydrogen bromide	HBr	010035-10-6	50 %	C	—	1/1	1/2	4/4	4/4	(4)	4/4	4/4	1/2	4/4	0/0	1/1	3/3	0/0	1/1	1/1	1/1	1/1	3/0	1/0	4/4	0/0	(4)	(4)	(4)	0/0	
Hydrogen bromide	HBr	010035-10-6	diluted	C	—	1/1	1/1	4/4	4/4	3/0	4/4	4/4																			



CHEMICALS	FORMULA	CAS-NR.	CONCENTRATION	HAZARD NOTE	FLAMMABLE	thermoplastics														fluoroplastics		elastomers		metals		COMMENT					
						HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HART	PVC WEICH	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FKM / FKM	NBR		SI	AL	V2A	V4A	
Lemongrass oil	—	008007-02-1	—	(Xi)	—	0/0	0/0	(2)	(3)	(0)	(2)	(3)	4/4	0/0	0/0	0/0	1/1	0/0	(1)	(1)	(3)	4/4	(3)	(4)	0/0	(1)	(1)	(1)			
Ligroin	—	008032-32-4	—	F, Xn	X	0/0	0/0	(2)	1/0	(2)	(4)	(2)	(3)	3/3	0/0	0/0	0/0	1/1	0/0	(1)	1/1	1/1	4/4	1/0	1/0	0/0	1/1	1/1	1/1	petroleum ether	
Lime chloride	[3 x CaCl(OCl) + Ce—	—	aqueous	?	—	0/0	0/0	4/4	(2)	3/0	0/0	4/4	(2)	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/1	4/4	0/0	4/4	2/0L	2/0L	1/1	chloride of lime, bleach	
Lime chloride	[3 x CaCl(OCl) + Ce—	—	—	O, C	—	0/0	0/0	4/4	(2)	3/0	0/0	4/4	1/1	1/3	0/0	0/0	0/0	1/1	0/0	(1)	1/1	1/1	1/0	1/1	4/4	0/0	4/4	2/0L	2/0L	1/1	chloride of lime, bleach
Limonene, DL-	C <sub>10</sub> H <sub>16</sub>	000138-86-3	—	Xn	X	0/0	0/0	(1)	(3)	(2)	(4)	(1)	(3)	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(1)	4/4	1/0	3/3	0/0	1/1	1/1	1/1			
Linseed oil	—	008001-26-1	techn. pure	—	—	1/1	1/3	1/0	1/0	1/0	1/1	1/1	1/1	1/1	0/0	1/3	1/0	1/1	0/0	(1)	1/1	1/1	4/4	1/1	1/1	0/0	(1)	1/1	1/1	1/1	
Liqueurs	—	—	—	—	—	1/0	0/0	(2)	1/0	1/0	0/0	(2)	1/0	0/0	0/0	1/0	0/0	0/0	(1)	1/1	1/1	1/0	1/0	1/1	0/0	(1)	1/1	1/1	1/1	1/1	
Lithium bromide	LiBr	007550-35-8	—	Xn	—	1/1	1/1	(3)	(2)	1/0	0/0	(2)	1/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	(1)	1/0	1/0	1/0	0/0	(3)	0/0	0/0			
Lube oils	—	—	—	?	—	1/3	2/3	(2-3)	(1)	(2)	0/0	(2)	3/0	0/0	0/0	1/1	1/3	0/0	(1)	1/1	1/1	4/4	1/1	1/0	0/0	1/1	1/1	1/1	1/1	0/0	
Lysol	—	—	—	T	—	0/0	0/0	(4)	(3)	0/0	0/0	(3)	1/3	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	(3)	(3)	0/0	(3)	1/1	1/1	1/1	1/1	1/1	disinfectant, cresol + soap
Machine oil	—	—	100 %	?	—	0/0	1/4	(1)	(2)	1/0	0/0	1/1	1/3	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	4/4	1/0	1/0	0/0	1/1	1/1	1/1	1/1	1/1	
Magnesium bromide	MgBr <sub>2</sub>	007789-48-2	—	Xi	—	1/1	1/1	(2)	(2)	(1)	0/0	1/1	1/1	1/1	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/1	(1)	(2)	0/0	(3)	0/0	0/0			
Magnesium carbonate	MgCO <sub>3</sub>	000546-93-0	saturated	—	—	1/1	1/1	1/0	1/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	
Magnesium chloride	MgCl <sub>2</sub>	007786-30-3	aqueous	Xi	—	1/1	1/1	1/0	1/0	1/0	1/2	1/1	1/1	1/0	1/1	1/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/0	1/1	1/1	1/0L	1/0L	1/1	
Magnesium chlorite	Mg(ClO <sub>2</sub> ) <sub>2</sub>	??	—	O	—	0/0	0/0	0/0	0/0	0/0	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	0/0	0/0	1/1	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	
Magnesium hydroxide	Mg(OH) <sub>2</sub>	001309-42-8	saturated	—	—	1/1	1/1	1/0	(2)	1/1	1/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	2/0	1/1	1/1	1/1	1/1	0/0		
Magnesium iodide	MgI <sub>2</sub>	010377-58-9	—	(Xn)	—	1/1	1/1	(2)	(2)	(2)	0/0	1/1	1/1	0/0	0/0	0/0	0/0	1/1	1/1	1/1	(1)	1/1	(1)	(2)	0/0	(2)	0/0	0/0			
Magnesium nitrate	Mg(NO <sub>3</sub> ) <sub>2</sub>	010377-60-3	saturated	O, Xi	—	1/1	1/1	1/0	(2)	(1)	1/0	1/1	1/1	1/0	0/0	1/1	1/0	0/0	1/1	1/1	1/1	1/1	1/1	(1)	(2)	0/0	1/0	1/0	1/1	Nitric acid, magnesium salt;	
Magnesiumsulfat	MgSO <sub>4</sub>	007487-88-9	each	—	—	1/1	1/1	1/0	1/0	1/0	1/0	1/1	1/1	1/0	1/1	1/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	2/0	0/0	1/1	1/1	1/1	1/1		
Maize-germ oil	—	008001-30-7	techn. pure	—	—	1/3	0/0	(2)	(1)	1/0	0/0	(2)	1/3	1/1	0/0	3/0	0/0	1/1	0/0	(1)	1/1	1/1	4/4	1/1	1/0	0/0	(1)	1/1	1/1	corn oil	
Maleic acid	C <sub>4</sub> H <sub>2</sub> O <sub>4</sub>	000110-16-7	saturated	Xn	—	1/1	1/1	4/4	(3)	0/0	0/0	(3)	1/1	0/0	0/0	1/3	1/0	0/0	1/1	1/1	1/1	1/1	4/4	1/1	4/4	0/0	1/1	1/1	1/1	1/1	
Maleic acid	C <sub>4</sub> H <sub>2</sub> O <sub>4</sub>	000110-16-7	aqueous	Xn	—	1/1	1/1	4/4	(3)	0/0	0/0	(3)	1/1	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	4/4	1/1	1/0	0/0	1/1	1/1	1/1	1/1	
Margarine	—	—	—	—	—	0/0	0/0	(2)	1/0	1/0	0/0	(2)	1/1	1/0	0/0	0/0	0/0	1/1	0/0	(1)	1/1	1/1	4/4	1/0	1/0	0/0	(1)	1/1	1/1		
Menthol	C <sub>10</sub> H <sub>20</sub> O	000089-78-1	solid	Xi	—	1/3	3/4	3/0	3/4	0/0	0/0	(2)	1/3	4/4	0/0	0/0	0/0	0/0	(1)	1/1	1/1	3/0	1/0	3/3	0/0	(1)	1/0	1/0			
Mercuric chloride	HgCl <sub>2</sub>	007487-94-7	aqueous	T+, C	—	1/1	1/1	4/4	1/0	(2)	1/1	3/0	1/1	1/3	1/0	1/3	1/0	1/1	1/1	1/1	1/1	1/1	1/0	1/1	1/3	0/0	4/4	(4)	(4)	1/1	
Mercuric cyanide	C <sub>2</sub> HgN <sub>2</sub>	000592-04-1	saturated	T+	—	1/1	1/1	(3)	(2)	(2)	0/0	(3)	1/1	0/0	0/0	1/3	0/0	0/0	(1)	1/1	1/1	1/1	(1)	1/1	(2)	0/0	4/4	1/0	1/1	1/1	
Mercuric nitrate	Hg(NO <sub>3</sub> ) <sub>2</sub>	010045-94-0	saturated	(T+)	—	1/1	1/1	1/0	(2)	(2)	0/0	(3)	1/1	1/0	0/0	1/3	0/0	(1)	1/1	1/1	1/1	1/0	1/1	1/3	0/0	4/4	1/1	1/1	1/1	1/1	
Mercury	Hg	007439-97-6	pure	T	—	1/1	1/1	1/0	1/1	1/1	1/1	1/1	1/1	1/1	3/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	(3)	1/1	1/1	1/1	
Mesityl oxide	C <sub>8</sub> H <sub>10</sub> O	000141-79-7	—	Xn	X	0/0	0/0	(2)	(4)	(4)	(4)	(2)	(3)	4/4	0/0	0/0	0/0	4/4	0/0	(1)	1/1	0/0	3/0	4/4	4/4	0/0	(1)	(1)			
Methacetone	-> see: Pentanone, 3-	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—
Methacrylic acid	C <sub>4</sub> H <sub>6</sub> O <sub>2</sub>	000079-41-4	—	C	—	1/0	1/1	4/4	4/4	0/0	0/0	4/4	1/1	0/0	0/0	0/0	0/0	0/0	(1)	1/1	(3)	3/0	4/4	4/4	0/0	(4)	0/0	0/0			
Methane	CH <sub>4</sub>	000074-82-8	techn. pure	F+	X	1/0	0/0	1/0	1/0	1/0	0/0	1/0	1/0	0/0	0/0	1/0	0/0	0/0	0/0	1/1	1/1	1/1	4/4	1/0	1/0	0/0	1/1	1/1	1/1	0/0	
Methanoic acid	-> see: Formic acid	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—
Methenamine	-> see: Hexamethylenetetramine	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—
Methoxy butanol	C <sub>5</sub> H <sub>12</sub> O <sub>2</sub>	—	100 %	?	X	0/0	1/3	(2)	(3)	0/0	0/0	(2)	1/3	0/0	0/0	0/0	0/0	0/0	(1)	1/1	(2)	3/0	1/0	1/0	0/0	(1)	(1)	(1)		isomer not indicated in the source	
Methoxyethane	C <sub>3</sub> H <sub>8</sub> O	000540-67-0	100 %	(F+)	X	0/0	3/0	(1)	(4)	0/0	(4)	(2)	(3)	4/4	0/0	0/0	0/0	0/0	(1)	1/0	(2)	4/4	4/4	4/4	0/0	1/1	(1)	(1)		Methyl ethyl ether;	
Methoxyethyl oleate	-> see: Ethylene glycol monomethyl ether oleate	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—
Methyl acetate	C <sub>3</sub> H <sub>6</sub> O <sub>2</sub>	000079-20-9	techn. pure	F	X	1/0	1/1	1/0	4/4	3/0	(4)	2/0	1/3	4/4	0/0	4/4	4/4	4/4	0/0	1/0	1/1	1/4	3/0	4/4	4/4	0/0	(1)	1/1	1/1	0/0	
Methyl acrylate	C <sub>5</sub> H <sub>8</sub> O <sub>2</sub>	000096-33-3	—	F, Xn	X	0/0	0/0	(2)	4/4	(4)	(4)	(2)	(2)	4/4	0/0	0/0	0/0	0/0	(1)	(1)	(3)	4/4	4/4	4/4	0/0	(1)	(1)	(1)			
Methyl alcohol	CH <sub>3</sub> O	000067-56-1	—	F, T	X	1/1	1/1	2/0	4/4	1/0	1/1	1/1	3/4	3/3	1/3	3/3	3/4	1/1	1/1	1/1	1/1	1/0	3/4	3/3	0/0	1/0	1/1	1/1			
Methyl amine	CH <sub>5</sub> N	000074-89-5	32 %	F+, C	X	1/0	1/0	4/4	4/4	0/0	0/0	1/0	1/0	0/0	0/0	3/0	4/4	0/0	(1)	1/0	3/0	1/0	4/4	4/4	0/0	1/0	1/0	1/0	0/0		
Methyl benzene	C <sub>7</sub> H <sub>8</sub>	000108-88-3	—	F, Xn	X	3/4	3/4	1/0	4/4	1/0	3/3	1/3	3/4	4/4	4/4	4/4	4/4	4/4	1/1	1/1	1/0	1/1	4/4	3/3	4/4	0/0	1/1	1/1	1/1	1/1	
Methyl bromide	CH <sub>3</sub> Br	000074-83-9	techn. pure	T	—	3/0	4/4	1/0	(3)	0/0	0/0	1/0																			

CHEMICALS	FORMULA	CAS-NR.	CONCENTRATION	HAZARD NOTE	thermoplastics																	fluoroplastics		elastomers		metals		COMMENT							
					FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HART	PVC WEICH	SAN	ECTFE / ETEF	PEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL		V2A	V4A	Hastelloy C				
Methyl sulfuric acid	CH <sub>3</sub> SO <sub>4</sub>	000077-78-1	50 %	(C)		0/0	1/1	4/4	(4)	(4)	(4)	(4)	(3)	1/1	4/4	0/0	3/0	0/0	0/0	0/0	0/0	(1)	1/1	(2)	1/0	4/4	4/4	0/0	(4)	0/0	0/0	4/4			
Methyl sulfuric acid	CH <sub>3</sub> SO <sub>4</sub>	000077-78-1	aqueous	(C)		0/0	0/0	4/4	(4)	(4)	(4)	(4)	0/0	4/4	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	(2)	1/0	4/4	4/4	0/0	(4)	0/0	0/0	4/4			
Methyl-1-propanol, 2-	-> see: Isobutanol																																		
Methylchloroacetate	C <sub>2</sub> H <sub>3</sub> ClO <sub>2</sub>	000096-34-4	techn. pure	T/Xi	X	1/1	0/0	(3)	4/4	(4)	(4)	(4)	(3)	1/1	4/4	0/0	3/0	0/0	0/0	0/0	0/0	(1)	1/1	(1)	1/4	3/0	4/4	4/4	0/0	3/4	0/0	0/0	0/0		
Methylcyclohexane	C <sub>6</sub> H <sub>14</sub>	000108-87-2		F, Xn	X	3/0	3/0	(2)	(2)	1/0	(4)	(2)	3/0	0/0	0/0	0/0	0/0	0/0	1/1	0/0	(1)	1/0	(1)	4/4	(1)	4/4	0/0	1/1	1/1	1/1	0/0				
Methylcyclopentane	C <sub>5</sub> H <sub>12</sub>	000096-37-7		F	X	0/0	0/0	(2)	(2)	1/0	(4)	(2)	(3)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	(1)	4/4	1/0	4/4	0/0	1/1	1/1	1/1				
Methylene chloride	CH <sub>2</sub> Cl <sub>2</sub>	000075-09-2		Xn		4/4	4/4	3/4	4/4	4/4	3/4	3/0	3/4	4/4	4/4	4/4	4/4	4/4	2/2	1/1	1/1	1/3	4/4	3/3	4/4	0/0	4/4	1/1L	1/1L	1/1L					
Methylglycol acetate	C <sub>4</sub> H <sub>10</sub> O <sub>3</sub>	000110-49-6		T		0/0	0/0	1/0	(3)	0/0	0/0	(2)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	(2)	3/0	4/4	4/4	0/0	(1)	(1)					
Methylsiloxane	-> see: Propylene oxid																																		
Methylpropyl acetate, 2-	-> see: Isobutyl acetate																																		
Milk	-																																		
Mineral oil		008012-95-1		(Xn)		1/1	2/4	(1)	1/2	1/1	1/2	1/1	1/3	1/1	1/1	1/2	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/1	4/4	1/1	2/2	0/0	1/1	1/1	1/1	0/0			
Mineral water	-																																		
Molasses	-																																		
Molasses wort	-																																		
Monochlorobenzene (MCB)	-> see: Chlorobenzene																																		
Monochloroethane	C <sub>2</sub> H <sub>5</sub> Cl	000075-00-3		F+, Xn	X	3/3	3/4	1/0	4/4	0/0	3/4	1/0	3/4	4/4	4/4	4/4	4/4	4/4	1/1	1/1	1/0	1/1	4/4	3/0	4/4	0/0	(3)	(1/1L) <sup>1)</sup>	(1/1L) <sup>1)</sup>	0/0			Ethyl chloride; Chloroethane, 1- <sup>1)</sup> Water-free! If even traces of hydrochloric acid (HCl) are split off by moisture, there is a risk of pitting, crevice and stress corrosion cracking.		
Morpholine	C <sub>2</sub> H <sub>5</sub> NO	000110-91-8	techn. pure	C, Xn	X	1/1	1/1	(3)	(3)	0/0	0/0	(2)	1/1	0/0	0/0	4/4	4/4	0/0	0/0	(1)	1/1	1/3	3/0	2/3	4/4	0/0	1/0	(1)	(1)	0/0					
Motor oil	-																																		
Mowilith D	-																																		
Muscate	-																																		
Mustard	-																																		
Naphtha	-																																		
Naphthalene	C <sub>10</sub> H <sub>8</sub>	000091-20-3	100 %	F, Xn	X	0/0	1/3	1/0	(3)	0/0	0/0	1/2	1/3	3/4	1/0	4/4	4/4	1/4	0/0	(1)	1/1	1/3	4/4	1/1	4/4	0/0	1/1	1/1	1/1	0/0					
Naphthalene (in alcohol)	-																																		
Neon	Ne	007440-01-9				0/0	0/0	1/0	(1)	1/1	0/0	1/1	(1)	0/0	0/0	0/0	0/0	0/0	1/1	(1)	1/1	1/1	1/1	1/1	1/0	0/0	1/1	1/1	1/1	1/1					
Nickel acetate	C <sub>2</sub> H <sub>3</sub> NiO <sub>4</sub>	000373-02-4	aqueous	(T, N)		1/1	1/1	(3)	(2)	(1)	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	1/0	(3)	3/0	0/0	4/4	0/0	0/0						
Nickel dichloride	NiCl <sub>2</sub>	007718-54-9	saturated	T		1/1	1/1	1/0	(2)	(1)	0/0	2/0	1/1	0/0	0/0	1/1	1/1	0/0	0/0	1/1	1/1	1/1	1/0	1/0	1/0	0/0	4/4	2/0L	2/0L	1/1					
Nickel dichloride	NiCl <sub>2</sub>	007718-54-9	aqueous	T		1/1	1/1	(3)	(2)	(1)	0/0	2/0	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/0	1/0	0/0	4/4	2/0L	2/0L	1/1					
Nickel sulfate	NiSO <sub>4</sub>	007786-81-4	saturated	Xn		1/1	1/1	1/0	1/0	(1)	1/0	2/0	1/1	1/1	0/0	0/0	1/1	1/3	1/1	0/0	1/1	1/1	1/1	1/0	1/1	1/1	0/0	4/4	1/1	1/1	1/1				
Nickel sulfate	NiSO <sub>4</sub>	007786-81-4	aqueous	Xn		1/1	1/1	(3)	1/0	(1)	0/0	2/0	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/1	1/1	0/0	4/4	1/1	1/1	1/1					
Nickelous nitrate	Ni(NO <sub>3</sub> ) <sub>2</sub>	013138-45-9	saturated	(O <sub>2</sub> , Xn)		1/1	1/1	(3)	(2)	(1)	0/0	(2)	1/1	1/0	1/0	1/1	1/1	0/0	0/0	1/1	1/1	1/1	1/0	1/0	1/0	0/0	4/4	1/0	1/0	1/1					
Nicotine	C <sub>10</sub> H <sub>14</sub> N <sub>2</sub>	000054-11-5		T+		1/0	1/0	(3)	(3)	0/0	0/0	(2)	1/0	1/0	0/0	1/0	0/0	0/0	(1)	(1)	(2)	1/0	1/0	1/1	0/0	(1)	(1)	(1)	(1)	0/0					
Nicotinic acid	C <sub>6</sub> H <sub>7</sub> NO <sub>2</sub>	000059-67-6	diluted	Xi		1/1	1/1	(3)	(2)	0/0	0/0	(3)	1/0	0/0	0/0	1/1	0/0	0/0	1/1	(1)	(2)	(2)	(3)	(2)	0/0	(3)	0/0	0/0	0/0						
Nitric acid	HNO <sub>3</sub>	007697-37-2	1-10 %	C		1/1	1/1	4/4	1/2	(2)	1/1	4/4	1/1	2/4	1/3	1/2	0/0	1/3	1/1	1/1	1/1	1/1	2/0	1/1	4/4	0/0	3/4	1/1	1/1	1/1					
Nitric acid	HNO <sub>3</sub>	007697-37-2	50 %	C+		2/4	3/4	4/4	4/4	(2)	2/4	4/4	3/4	4/4	2/3	2/3	0/0	0/3	1/1	1/1	1/1	1/1	4/4	1/0	4/4	0/0	4/4	1/2	1/2	1/2					
Nitric acid	HNO <sub>3</sub>	007697-37-2	66 %	C+		2/4	3/4	4/4	4/4	(4)	2/3	4/4	4/4	4/4	3/4	0/0	0/0	1/1	1/1	1/1	1/1	4/4	1/0	4/4	0/0	4/4	1/2	1/2	1/2						
Nitric acid	HNO <sub>3</sub>	007697-37-2	100 %	O, C+		4/4	4/4	4/4	4/4	(4)	0/0	4/4	4/4	0/0	0/0	4/4	0/0	4/4	0/0	1/1	4/4	4/4	4/4	4/4	0/0	1/1	2/3	3/3	?						
Nitric acid	HNO <sub>3</sub>	007697-37-2	70 %	O, C+		2/4	3/4	4/4	4/4	(4)	2/3	4/4	4/4	4/4	3/4	0/0	0/0	1/1	1/1	1/1	1/1	4/4	2/3	4/4	0/0	4/4	1/2	1/2	1/2						
Nitric acid	-> see: Ammonium nitrate																																		
Nitric acid, magnesium salt	-> see: Magnesium nitrate																																		
Nitric acid, potassium salt	-> see: Potassium nitrate																																		
Nitro benzoic acid	C <sub>7</sub> H <sub>5</sub> NO <sub>4</sub>			(Xn)		1/0	1/0	(3)	(3)	0/0	0/0	(3)	1/0	0/0	0/0	1/0	0/0	0/0	0/0	(1)	(1)	(2)	3/0	(3)	(2)	0/0	(3)	0/0	0/0					isomer not indicated in the source	
Nitro reducer	-																																		
Nitrobenzene	C <sub>6</sub> H <sub>5</sub> NO <sub>2</sub>	000098-95-3		T		3/4	4/4	4/4	4/4	1/0	4/4	3/0	2/4	4/4	4/4	4/4	4/4	1/2	1/1	1/1	1/1	4/4	4/4	4/4	0/0	(1)	1/1	1/1	1/1	1/1					
Nitroethane	C <sub>2</sub> H <sub>5</sub> NO <sub>2</sub>	000079-24-3		Xn	X	0/0	0/0	(4)	(4)	0/0	0/0	(3)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(3)	3/0	4/4	4/4	0/0	(1)	(1)	(1)						
Nitrogen	N <sub>2</sub>	007727-37-9				0/0	0/0	1/0	1/1	0/0	1/1	0/0	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/0	0/0	1/1	1/1	1/1						
Nitrogen hydride	-> see: Hydrazine																																		
Nitrogen tetroxide	NO <sub>2</sub>	010544-72-6		(O), T+, C		0/0	0/0	3/0	(3)	1/0	0/0	4/4	1/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(2)	4/4	4/4	4/4	0/0	(2)	(1)	(1)							
Nitroglycerine	C <sub>3</sub> H <sub>5</sub> (NO <sub>3</sub> ) <sub>3</sub>	000055-63-0	diluted	(E, T+)		0/0	0/0	(3)	(3)	0/0	0/0	(2)	(2)	0/0	0/0	3/0	4/4	0/0	0/0	(1)	1/0	(3)	1/0	1/0	4/4	0/0	0/0	0/0	0/0	0/0					
Nitrohydrochloric acid	HNO <sub>3</sub> + HCl	008007-56-5		C		4/4	4/4	4/4	4/4	3/3	4/4	4/4	4/4	4/4	4/4	3/4	1/1	(2)	1/1	3/0	4/4	4/4	4/4	0/0	4/4	4/4	4/4	4/4	4/4					aquea regia: mixture of hydrochloric acid and nitric acid	
Nitropropane	C <sub>3</sub> H <sub>7</sub> NO <sub>2</sub>			(T)		0/0	0/0	(3)	(4)	0/0	0/0	(3)	(2)	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(3)	3/0	4/4	4/4	0/0	(1)	(1)	(1)						isomer not indicated in the source	
Nitrose gases	-																																		
Nitrotoluene	C <sub>7</sub> H <sub>7</sub> NO <sub>2</sub>	001321-12-6	techn. pure	T		1/3	1/3	4/4	4/4	1/0	(4)	3/0	1/3	4/4	0/0	4/4	4/4	0/0	0/0	(1)	1/1	1/1	4/4	4/4	4/4	0/0	(1)	1/1	1/1					nitrogen monoxide + nitrogen dioxide	
Nitrous acid, sodium salt	-> see: Sodium nitrite																																		
Nitrous oxide	N <sub>2</sub> O	010024-97-2		(O)		0/0	0/0	(2)	(2)	(1)	0/0	(2)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(1)	2/0	1/0	1/0	0/0	1/1	(1)	(1)					nitric oxide	
Nonanol	-> see: Nonyl alcohol																																		
Nonyl alcohol	C <sub>9</sub> H <sub>20</sub> O	000143-08-8	100 %	Xn, Xi		0/0	1/1	(2)	(2)	(1)	0/0	(1)	1/1	1/0	0/0	0/0	0/0	1/1	0/0	(1)	(1)	(1)	1/0	1/0	3/3	0/0	(1)	(1)	(1)					Nonanol; Pelargonic alcohol; Octyl carbinol	
Nutmeg oil	-																																		



CHEMICALS	FORMULA	CAS-NR.	CONCENTRATION	HAZARD NOTE	thermoplastics																	fluoroelastics		elastomers		metals		COMMENT				
					FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HART	PVC WEICH	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL		V2A	V4A		
Octafluoropropane	C <sub>3</sub> F <sub>8</sub>	000076-19-7	?		0/0	0/0	1/0	2/3	(1)	1/1	1/0	1/1	4/4	2/3	3/4	3/3	1/1	1/1	1/1	(1)	(1)	1/0	1/0	1/0	1/0	0/0	(3)	0/0	0/0			
Octane	C <sub>8</sub> H <sub>18</sub>	000111-65-9		F, Xn	X	1/1	1/1	1/0	2/3	(1)	1/1	1/0	1/1	4/4	2/3	3/4	3/3	1/1	1/1	1/1	(1)	(1)	1/0	1/0	1/0	1/0	0/0	(3)	0/0	0/0		
Octyl carbinol	-> see: Nonyl alcohol																															
Octyl cresol ?	C <sub>15</sub> H <sub>24</sub> O	—	100 %	?		3/0	3/0	(3)	(4)	0/0	0/0	(3)	3/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	3/0	3/0	0/0	(1)	(1)	(1)	0/0	isomer not indicated in the source	
Oils and fats, vegetable	—	—	—	?		1/3	1/3	(2)	(2)	1/0	0/0	(2)	1/3	3/0	0/0	1/1	3/3	0/0	(1)	1/1	1/1	4/4	1/1	(2)	0/0	(1)	1/1	1/1	0/0			
Oils, essential	—	—	—	?		4/4	3/4	(2)	(3)	0/0	0/0	(2)	3/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(3)	4/4	(1-3)	(3)	0/0	1/1	(1)	(1)	0/0			
Oleic acid	C <sub>18</sub> H <sub>34</sub> O <sub>2</sub>	000112-80-1	techn. pure	Xi		1/3	1/3	1/0	1/0	1/0	0/0	2/0	1/3	1/3	0/0	1/1	0/0	1/3	0/0	(1)	1/1	1/1	4/4	2/2	3/0	0/0	1/1	1/1	1/1	0/0		
Oleic acid methyl ester	C <sub>19</sub> H <sub>36</sub> O <sub>2</sub>	000112-62-9	—	—		0/0	0/0	(2)	(3)	(2)	(4)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(1)	3/0	1/0	4/4	0/0	(1)	(1)	(1)	0/0			
Oleum	H <sub>2</sub> SO <sub>4</sub> x SO <sub>3</sub>	008014-95-7	10 % SO <sub>3</sub>	C+		4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	0/0	0/0	(1)	1/0	(3)	1/0	(3)	0/0	(3)	(1)	(1)	0/0	fuming sulfuric acid	
Oleum steams	—	—	small	?		4/4	0/0	4/4	(3)	0/0	0/0	4/4	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	1/0	(3)	1/0	(3)	0/0	(3)	(1)	(1)	0/0	sulfur trioxide		
Olive oil	—	008001-25-0	—	—		1/3	0/0	(2)	(2)	1/0	0/0	1/1	1/1	1/1	0/0	1/1	0/0	1/1	0/0	(1)	1/1	1/1	4/4	1/1	1/1	0/0	1/1	1/1	1/1	0/0		
Orange juice	—	—	—	—		1/1	1/1	(1)	1/0	1/0	0/0	(2)	1/1	1/0	0/0	0/0	0/0	1/1	1/1	1/1	(1)	(1)	(1)	(1)	0/0	(2)	(1)	(1)	0/0			
Orange oil	—	008028-48-6	—	Xn		(3)	(3)	1/0	(3)	0/0	(4)	1/0	(3)	4/4	0/0	0/0	0/0	0/0	0/0	(1)	1/1	(3)	4/4	(2)	(3)	0/0	(1)	(1)	0/0	mainly + limonene		
Orange oil, bitter	—	068916-04-1	—	?		2/3	3/4	(2)	3/3	1/0	3/3	(2)	2/3	4/4	3/3	3/4	0/0	0/0	1/1	1/1	(1)	(2)	4/4	(2)	(4)	0/0	(1)	(1)	(1)	0/0		
Oxacyclopentadiene	-> see: Furan																															
Oxalic acid	C <sub>2</sub> H <sub>2</sub> O <sub>4</sub> x 2H <sub>2</sub> O	000144-62-7	aqueous	Xn		1/1	1/1	4/4	(2)	(2)	0/0	4/4	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	(2)	1/0	1/1	3/3	0/0	1/0	2/3	1/3	1/2	Ethanedioic acid;	
Oxalic acid	C <sub>2</sub> H <sub>2</sub> O <sub>4</sub> x 2H <sub>2</sub> O	000144-62-7	—	Xn		1/1	1/1	3/4	1/0	0/0	1/1	4/4	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/3	1/0	1/1	3/3	0/0	1/0	2/3	1/3	1/3		
Oxygen	O <sub>2</sub>	007782-44-7	techn. pure	O		1/3	1/3	2/0	1/0	(1)	0/0	1/0	1/3	1/0	0/0	1/1	1/0	0/0	0/0	1/1	1/1	1/1	1/0	1/0	3/3	0/0	(2)	(1)	(1)	0/0		
Ozone	O <sub>3</sub>	010028-15-6	—	(O, T)		3/4	3/4	4/4	1/2	0/0	1/1	4/4	3/4	2/2	1/1	1/2	0/0	1/1	1/1	1/1	(1)	1/3	1/0	1/0	4/4	0/0	(2)	0/0	0/0	0/0		
Ozone-air-mixture	—	—	—	(O, T)		0/0	0/0	4/4	(2)	0/0	0/0	4/4	3/4	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	(2)	1/0	1/0	4/4	0/0	(2)	0/0	0/0	0/0		
Palm kernel oil	—	008023-79-8	—	—		0/0	0/0	1/0	(2)	1/0	0/0	(2)	1/3	1/1	0/0	0/0	0/0	0/0	(1)	1/1	1/1	4/4	1/0	1/1	0/0	(1)	1/1	1/1	1/1	0/0		
Palm oil	—	008002-75-3	—	—		1/3	0/0	1/0	(2)	1/0	0/0	(2)	1/3	0/0	0/0	1/0	0/0	1/1	0/0	(1)	1/1	1/1	4/4	1/0	1/1	0/0	(1)	1/1	1/1	0/0		
Palmitic acid	C <sub>16</sub> H <sub>32</sub> O <sub>2</sub>	000057-10-3	techn. pure	Xi		3/3	2/2	1/1	(2)	1/0	0/0	1/0	3/4	1/1	0/0	1/1	3/0	1/1	0/0	(1)	1/1	1/1	4/4	1/1	3/3	0/0	1/1	1/1	1/1	1/1	0/0	
Paraffin wax	—	008002-74-2	melted	(—)		0	0	0	(2)	0	0	(2)	0	0	0	0	0	0	0	(1)	1	0	4	2	1	0	1	1	1	1	0/0	
Paraffin-emulsion	—	—	—	?		1/3	0/0	1/0	(2)	(2)	0/0	(2)	1/3	0/0	0/0	1/0	0/0	0/0	0/0	(1)	1/1	1/1	(4)	1/0	1/1	0/0	(2)	(1)	(1)	0/0		
Paraffins	C <sub>n</sub> H <sub>2n+2</sub>	—	100 %	?		1/0	1/1	1/0	1/0	1/0	1/1	1/1	1/0	1/0	1/0	1/0	0/0	0/0	(1)	1/1	(1)	4/4	1/0	1/3	0/0	1/1	1/1	1/1	1/1	0/0		
Paraformaldehyde	(CH <sub>2</sub> O) <sub>n</sub> H <sub>2</sub> O	030525-89-4	—	F, T	X	0/0	0/0	0/0	(2)	1/0	0/0	(2)	1/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	3/0	1/0	3/3	0/0	(1)	(1)	(1)	0/0	Polyoxymethylene;		
Peanut oil	—	008002-03-7	—	—		0/0	0/0	0/0	(2)	1/0	0/0	(2)	1/1	1/1	0/0	0/0	1/1	0/0	(1)	1/1	(1)	4/4	1/0	1/0	0/0	(1)	(1)	(1)	0/0			
Pectin	—	009000-69-5	aqueous	—		1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	
Pectin	—	009000-69-5	—	—		1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	
Pelargonic alcohol	-> see: Nonyl alcohol																															
Penicillin	—	—	—	Xn		(1)	(1)	(2)	(1)	(1)	0/0	(1)	(2)	0/0	0/0	0/0	0/0	0/0	1/1	(1)	1/1	(1)	(1)	(2)	(1)	(2)	0/0	(1)	(1)	(1)	antibiotic	
Pentachlorobiphenyl	C <sub>12</sub> H <sub>2</sub> Cl <sub>5</sub>	—	—	Xn		0/0	0/0	1/0	(3)	0/0	0/0	(2)	4/4	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(2)	4/4	3/0	4/4	0/0	(1)	0/0	0/0	0/0			
Pentamethylenimine	-> see: Piperidine																															
Pentane, normal	C <sub>5</sub> H <sub>12</sub>	000109-66-0	—	F	X	1/3	1/3	1/0	1/0	(3)	1/0	(3)	(2)	0/0	0/0	0/0	0/0	1/0	0/0	(1)	(1)	(1)	4/4	1/0	1/2	0/0	1/1	1/1	1/1	0/0		
Pentanethiol, 1-	C <sub>5</sub> H <sub>12</sub> S	000110-66-7	—	Xn	X	0/0	0/0	(2)	(3)	0/0	(4)	(2)	(2)	0/0	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(2)	4/4	(3)	(4)	0/0	(2)	(1)	(1)	0/0		
Pentanol, 1-	C <sub>5</sub> H <sub>12</sub> O	000071-41-0	—	Xn	X	1/1	1/2	1/0	1/0	1/0	2/3	1/0	1/1	1/3	3/0	2/3	3/0	0/4	1/1	1/1	1/1	1/1	3/0	2/4	3/0	0/0	1/2	1/1	1/1	0/0	Amyl alcohol, n-; Butyl carbinol, n-; Pentyl alcohol, n-	
Pentanone, 3-	C <sub>5</sub> H <sub>10</sub> O	000096-22-0	—	F		2/2	2/3	(3)	4/4	(4)	2/3	1/0	2/2	4/4	4/4	4/4	0/0	4/4	2/3	1/1	1/1	(3)	(3)	(4)	(4)	0/0	(1)	(1)	(1)	0/0	Diethyl ketone; Dimethylacetone; Methacetone	
Pentyl alcohol, n-	-> see: Pentanol, 1-																															
Pepper	—	—	ground	?		0/0	0/0	(2)	1/0	(1)	0/0	(2)	(2)	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(1)	(2)	(2)	(2)	0/0	(1)	(1)	(1)	0/0		
Perchloric acid	HClO <sub>4</sub>	007601-90-3	70 %	E, O, C+		2/4	3/4	4/4	4/4	(4)	2/4	4/4	4/4	2/3	4/4	3/4	4/4	0/0	1/2	1/1	1/1	1/1	3/0	1/1	4/4	0/0	4/4	0/0	0/0	?		
Perchloric acid	HClO <sub>4</sub>	007601-90-3	20 %	Xi		0/0	1/3	4/4	3/0	0/0	0/0	4/4	1/3	0/0	0/0	1/3	3/0	0/0	0/0	1/1	1/1	1/1	2/0	1/1	4/4	0/0	4/4	0/0	0/0	1/1		
Perchlorotetradiene	C <sub>4</sub> Cl <sub>6</sub>	000087-68-3	—	T		0/0	0/0	(3)	4/4	0/0	(4)	1/0	(3)	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(2)	(3)	4/4	1/0	4/4	0/0	(3)	0/0	0/0	0/0		
Perchloroethylene	-> see: Tetrachloroethylene																															
Perfluorocyclobutane	C <sub>4</sub> F <sub>8</sub>	000115-25-3	—	?		0/0																										

CHEMICALS	FORMULA	CAS-NR.	CONCENTRATION	HAZARD NOTE	FLAMMABLE	thermoplastics													fluoroelastics		elastomers		metals		COMMENT										
						HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HART	PVC WEICH	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM		NBR	SI	AL	V2A	V4A					
Phosgene	COCl <sub>2</sub>	000075-44-5	gaseous	T+, C		0/0	3/0	1/0	(3)	0/0	0/0	(2)	3/4	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	(1)	(1)	(1)	(2)	0/0	0/0	(1)	(1)	0/0	0/0	salts of phosphoric acid	
Phosphates	—	—	aqueous	?		1/1	1/1	0/0	0/0	(1)	0/0	(2)	3/4	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	(1)	(1)	(1)	(1)	(1)	(1)	(1)	0/0	0/0	0/0	
Phosphine	PH <sub>3</sub>	007803-51-2	concentrated	F+, T+ X	X	0/0	0/0	1/0	(3)	0/0	0/0	1/0	(3)	0/0	0/0	1/0	0/0	0/0	0/0	0/0	1/0	1/1	1/0	1/0	1/0	1/0	4/4	0/0	(1)	0/0	0/0	0/0	0/0		
Phosphoric acid	H <sub>3</sub> PO <sub>4</sub>	007664-38-2	30 %	C		1/1	1/1	4/4	1/0	0/0	0/0	4/4	1/1	1/1	0/0	0/0	1/1	0/0	1/1	1/1	1/1	1/1	1/1	1/1	1/0	1/1	3/3	0/0	4/4	1/3	1/2	1/1	0/0		
Phosphoric acid	H <sub>3</sub> PO <sub>4</sub>	007664-38-2	85 %	C		1/1	1/1	4/4	1/2	0/0	1/2	4/4	1/2	1/2	1/1	1/2	1/1	1/2	1/1	1/1	1/1	1/1	1/1	1/1	3/0	1/1	4/4	0/0	4/4	2/4	1/3	1/1	0/0		
Phosphoric acid	H <sub>3</sub> PO <sub>4</sub>	007664-38-2	1-5 %	Xi		1/1	1/1	(3)	1/1	1/0	1/1	3/4	1/1	2/2	1/1	1/1	0/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/0	1/1	2/3	0/0	(4)	1/1	1/1	1/1	0/0		
Phosphoric acid	H <sub>3</sub> PO <sub>4</sub>	007664-38-2	20 %	Xi		1/1	1/1	4/4	(2)	0/0	0/0	4/4	1/1	0/0	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/1	3/3	0/0	4/4	1/3	1/2	1/1	0/0	0/0		
Phosphorus oxychloride	POCl <sub>3</sub>	010025-87-3	100 %	T, C		0/0	1/0	4/4	4/4	0/0	0/0	4/4	1/3	0/0	0/0	4/4	4/4	0/0	0/0	0/0	1/1	(2)	1/0	1/1	4/4	0/0	1/3	1/3L	1/3L	1/1	0/0	0/0	0/0		
Phosphorus oxychloride	POCl <sub>3</sub>	010025-87-3	100 %	T, C		0/0	1/0	4/4	4/4	0/0	0/0	4/4	1/3	0/0	0/0	4/4	4/4	0/0	0/0	0/0	1/1	(2)	1/0	1/1	4/4	0/0	1/3	1/3L	1/3L	1/1	0/0	0/0	0/0		
Phosphorus pentachloride	PCl <sub>5</sub>	010026-13-8	—	T+, C		0/0	1/0	4/4	4/4	0/0	0/0	4/4	1/1	0/0	0/0	4/4	4/4	0/0	0/0	0/0	1/1	1/1	(3)	(3)	4/4	0/0	1/1	1/3L	1/3L	1/1	0/0	0/0	0/0	0/0	
Phosphorus pentoxide	P <sub>2</sub> O <sub>5</sub>	001314-56-3	techn. pure	C		1/0	0/0	(4)	(3)	0/0	0/0	4/4	1/0	0/0	1/0	0/0	0/0	0/0	0/0	(1)	1/0	1/1	(3)	(2)	3/4	0/0	1/1	1/0	1/0	1/0	0/0	0/0	0/0	0/0	
Phosphorus trichloride	PCl <sub>3</sub>	007719-12-2	—	T, C		3/3	3/3	4/4	4/4	0/0	0/0	4/4	1/3	0/0	0/0	4/4	4/4	0/0	0/0	1/0	1/1	1/1	1/0	3/4	4/4	0/0	1/1	0/0	1/1	0/0	0/0	0/0	0/0	0/0	
Phthalic acid	C <sub>8</sub> H <sub>6</sub> O <sub>4</sub>	000088-99-3	saturated	Xi		1/1	1/1	3/3	(3)	1/0	1/0	1/1	1/0	1/0	1/4	0/0	1/1	0/0	1/1	1/1	1/1	1/1	1/0	2/3	4/4	0/0	1/1	1/1	1/1	1/1	1/1	1/1	0/0	0/0	
Phthalsäuremonoamylester ?	C <sub>18</sub> H <sub>16</sub> O <sub>4</sub>	??	—	(Xn)		0/0	0/0	(3)	(3)	0/0	0/0	(3)	(2)	0/0	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(2)	(2)	(2)	(3)	0/0	(1)	(1)	(1)	(1)	(1)	(1)	0/0	0/0	
Picric acid	C <sub>6</sub> H <sub>3</sub> N <sub>3</sub> O <sub>7</sub>	000088-89-1	1 % aqueous	T		1/0	1/0	3/0	(3)	0/0	0/0	(3)	1/1	0/0	0/0	1/0	4/4	0/0	0/0	1/0	1/1	3/0	1/0	3/4	0/0	1/0	1/0	1/0	1/0	1/0	1/0	1/0	0/0	0/0	
Pine oil	—	008023-99-2	—	?		0/0	0/0	1/0	(3)	0/0	(4)	(2)	1/1	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(3)	4/4	1/0	1/0	0/0	1/1	(1)	(1)	(1)	(1)	0/0	0/0	0/0	0/0
Pineapple juice	—	—	—	—		1/1	1/1	1/0	(2)	1/0	0/0	(2)	1/1	1/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	(1)	(1)	(2)	(1)	0/0	(1)	(1)	(1)	(1)	(1)	(1)	0/0	0/0	
Pink	—	—	ground	?		0/0	0/0	(2)	4/4	(1)	0/0	(2)	(2)	4/4	0/0	0/0	0/0	4/4	0/0	(1)	1/1	(2)	(2)	(2)	(2)	0/0	(1)	(1)	(1)	(1)	(1)	0/0	0/0	0/0	
Piperidine	C <sub>5</sub> H <sub>11</sub> N	000110-89-4	—	F, T, C		0/0	0/0	(3)	(3)	0/0	0/0	(2)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	4/4	4/4	0/0	(1)	(1)	(1)	(1)	(1)	(1)	0/0	0/0	0/0
Plasticiser	—	—	—	?		1/3	1/3	(2)	(3)	0/0	0/0	(2)	1/3	0/0	0/0	0/0	0/0	3/3	0/0	(1)	(1)	0/0	(2-3)	0/0	4/4	0/0	(1)	(1)	(1)	(1)	(1)	(1)	0/0	0/0	
Polish remover	—	—	—	?	(X)	0/0	0/0	(2)	4/4	0/0	(4)	(2)	1/3	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	(3)	(3)	4/4	0/0	(1)	(1)	(1)	(1)	0/0	0/0	0/0	0/0	
Polyester resins	—	—	—	(Xn)		3/4	3/4	1/0	4/4	1/0	0/0	(2)	3/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	(3)	4/4	0/0	(1)	(1)	(1)	(1)	(1)	(1)	0/0	0/0	
Polyethylene glycol	HO-(C <sub>2</sub> H <sub>4</sub> O) <sub>n</sub> -H	025322-68-3	100 %	(—)		1/1	1/1	(3)	0/0	0/0	0/0	1/0	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	(2-3)	(2)	(3)	0/0	(1)	(1)	(1)	(1)	0/0	0/0	0/0	0/0	
Polyoxymethylene	-> see: Paraformaldehyde	—	—	—		—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	
Polyran M25 N	—	—	80°C	?		0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	3	0	0	(1)	(1)	(1)	(1)	lubricating oil	
Polyran M400	—	—	80°C	?		0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	(1)	(1)	(1)	(1)	lubricating oil	
Polysolvan O	C <sub>8</sub> H <sub>12</sub> O <sub>3</sub>	007397-62-8	100 %	Xi		0/0	1/1	(2)	(3)	1/0	0/0	1/0	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0
Potassium acetate	C <sub>2</sub> H <sub>3</sub> KO <sub>2</sub>	000127-08-2	aqueous	Xi		1/1	1/1	1/0	(1)	(2)	0/0	1/1	1/1	0/0	0/0	1/0	1/0	0/0	1/1	1/1	1/0	1/1	1/1	3/0	3/3	0/0	1/3	1/1	1/1	1/1	0/0	0/0	0/0	0/0	
Potassium bisulfate	KHSO <sub>4</sub>	007646-93-7	aqueous	(C)		1/1	1/1	4/4	1/0	(2)	0/0	2/0	1/1	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/0	1/0	1/0	1/0	1/0	4/4	4/4	1/1	0/0	0/0	0/0	0/0	
Potassium bisulfate	KHSO <sub>4</sub>	007646-93-7	—	C		1/1	1/1	4/4	1/0	0/0	0/0	2/0	1/1	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/1	1/0	1/0	1/0	1/0	1/0	4/4	4/4	?	0/0	0/0	0/0	0/0	
Potassium bitartrate	C <sub>4</sub> H <sub>4</sub> KO <sub>6</sub>	000868-14-4	saturated	Xi		1/1	1/1	(2)	(2)	0/0	0/0	(2)	1/1	0/0	0/0	1/0	1/0	0/0	1/1	1/1	1/1	(2)	(1)	(1)	0/0	(4)	1/3	1/2	0/0	0/0	0/0	0/0	0/0	0/0	
Potassium borate	KBO <sub>2</sub>	012228-88-5	10 %	(Xn)		1/1	1/1	1/0	(2)	(2)	0/0	1/1	1/1	0/0	0/0	1/3	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/0	1/0	1/0	1/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	
Potassium borate	KBO <sub>2</sub>	012228-88-5	aqueous	(Xn)		1/1	1/1	1/0	(2)	(2)	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/0	1/0	1/0	1/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	
Potassium bromate	KBrO <sub>3</sub>	007758-01-2	saturated	O, T		1/3	1/3	(2)	1/0	0/0	0/0	(2)	1/1	1/1	0/0	1/3	0/0	1/1	0/0	(1)	1/1	1/1	1/0	1/1	1/0	1/0	0/0	(2)	0/0	0/0	0/0	0/0	0/0	0/0	
Potassium bromate	KBrO <sub>3</sub>	007758-01-2	aqueous	O, T		0/0	0/0	(2)	0/0	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/1	1/1	0/0	(2)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	
Potassium bromide	KBr	007758-02-3	each	Xn		1/1	1/1	3/0	1/0	(1)	1/0	1/1	1/1	1/1	0/0	1/3	1/0	1/1	0/0	1/1	1/1	1/1	1/0	1/1	1/0	1/0	1/0	1/0	1/0L	1/0L	1/1	0/0	0/0	0/0	
Potassium carbonate	K <sub>2</sub> CO <sub>3</sub>	000584-08-7	saturated	Xn		1/1	1/1	1/1	3/3	(2)	1/1	1/1	1/1	1/1	0/0	1/1	1/1	1/1	0/0	1/1	1/1	1/3	1/0	1/0	1/0	1/0	1/0	4/4	1/1	1/1	1/1	1/1	1/1	1/1	
Potassium carbonate	K <sub>2</sub> CO <sub>3</sub>	000584-08-7	aqueous	Xn		1/1	1/1	1/0	(2)	(2)	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/0	1/0	1/0	1/0	4/4	1/1	1/1	1/1	1/1			



CHEMICALS	thermoplastics												fluoroplastics		elastomers		metals		COMMENT												
	FORMULA	CAS-NR.	CONCENTRATION	HAZARD NOTE	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HART	PVC WEICH	SAN		ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FKM / FKM	NBR	SI	AL	V2A	V4A	Haselloy C
Soaps, liquid	—	—	—	—	1/1	1/1	1/0	(2)	(1)	0/0	1/1	1/1	0/0	0/0	1/3	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/1	1/1	0/0	(3)	1/1	1/1	1/1		
Soapy solution	—	—	each	(—)	1/1	0/0	4/4	(2)	1/1	0/0	1/1	1/1	0/0	0/0	1/3	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/1	1/1	0/0	(3)	1/1	1/1	1/1		
Sodium acetate	C <sub>2</sub> H <sub>3</sub> NaO <sub>2</sub>	000127-09-3	each	—	1/1	1/1	1/0	1/2	(1)	1/1	1/1	1/1	2/2	1/1	2/3	3/0	1/1	1/1	1/1	1/1	1/0	(3)	3/3	0/0	1/1	1/1	1/1	1/1	1/1	Acetic acid sodium salt;	
Sodium benzoate	C <sub>6</sub> H <sub>5</sub> NaO <sub>2</sub>	000532-32-1	36 %	Xn	1/1	1/1	1/0	(2)	(2)	0/0	(1)	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/0	(1)	1/1	0/0	(1)	(1)	(1)	(1)	1/1	
Sodium benzoate	C <sub>6</sub> H <sub>5</sub> NaO <sub>2</sub>	000532-32-1	aqueous	Xn	1/1	1/1	(2)	(2)	(1)	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/1	0/0	1/1	1/0	1/0	1/0	1/1		
Sodium benzoate	C <sub>6</sub> H <sub>5</sub> NaO <sub>2</sub>	000532-32-1	aqueous	Xn	1/1	1/1	1/0	(2)	(1)	0/0	1/1	1/1	1/1	0/0	1/3	0/0	1/1	1/1	1/1	1/1	1/1	1/0	1/0	1/1	0/0	1/1	1/0	1/0	1/1		
Sodium bicarbonate	NaHCO <sub>3</sub>	000144-55-8	aqueous	—	1/1	1/1	1/0	1/0	1/0	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	1/1	1/1	1/1	1/1		
Sodium bisulfate	NaHSO <sub>4</sub>	007681-38-1	10 %	(C)	1/1	1/1	4/4	1/0	1/0	0/0	2/0	1/1	0/0	0/0	1/3	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/0	1/3	0/0	1/3	1/2	1/1	1/1		
Sodium bisulfate	NaHSO <sub>4</sub>	007681-38-1	each	(C)	1/1	1/1	1/0	1/0	0/0	(3)	1/1	1/3	0/0	1/4	0/0	1/1	1/1	1/1	1/1	1/1	1/1	1/0	1/0	1/3	0/0	1/3	(2)	1/1	1/1		
Sodium bisulfite	NaHSO <sub>3</sub>	007631-90-5	aqueous	Xn	1/1	1/1	1/0	(2)	1/0	0/0	4/4	1/1	0/0	0/0	0/0	0/0	(1)	1/1	1/1	1/1	1/0	1/0	1/0	0/0	1/0	1/0	1/1	1/1	1/1		
Sodium borate	Na <sub>2</sub> B <sub>4</sub> O <sub>7</sub> · x H <sub>2</sub> O	001303-96-4	saturated	Xi	1/1	1/1	1/0	1/0	(2)	1/0	1/1	1/1	1/1	1/0	1/3	1/0	1/1	1/1	1/1	1/1	1/1	1/1	1/0	3/3	0/0	1/3	1/1	1/1	1/1		
Sodium borate	Na <sub>2</sub> B <sub>4</sub> O <sub>7</sub> · x H <sub>2</sub> O	001303-96-4	aqueous	Xi	1/1	1/1	1/0	(2)	1/0	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/0	1/0	0/0	1/3	1/1	1/1	1/1		
Sodium bromate	NaBrO <sub>3</sub>	007789-38-0	each	O, T	1/0	1/3	(3)	(2)	0/0	0/0	1/1	1/1	1/1	0/0	1/0	0/0	1/1	0/0	(1)	1/1	1/1	(2)	(1)	1/3	0/0	1/1	1/1L	1/1L	0/0		
Sodium bromide	NaBr	007647-15-6	each	Xi	1/1	1/1	1/0	(2)	(1)	0/0	1/1	1/1	1/1	0/0	1/3	0/0	1/1	1/1	1/1	1/1	1/1	(1)	(1)	1/3	0/0	4/4	0/0	0/0	0/0		
Sodium carbonate	Na <sub>2</sub> CO <sub>3</sub>	000497-19-8	saturated	Xi	1/1	1/1	1/0	1/0	0/0	1/0	1/1	1/1	1/1	1/0	1/1	1/1	1/1	1/1	1/1	1/1	1/3	1/1	1/1	0/0	3/4	1/1	1/1	1/1	1/1		
Sodium carbonate	Na <sub>2</sub> CO <sub>3</sub>	000497-19-8	aqueous	Xi	1/1	1/1	1/0	1/0	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/3	1/1	1/1	1/1	0/0	3/4	1/1	1/1	1/1		
Sodium carbonate	Na <sub>2</sub> CO <sub>3</sub>	000497-19-8	Xi	Xi	1/1	1/1	1/0	1/0	0/0	1/1	1/1	2/0	0/0	1/1	0/0	1/2	1/1	1/1	1/1	1/3	1/1	1/1	1/1	0/0	3/4	1/1	1/1	1/1	1/1		
Sodium chlorate	NaClO <sub>3</sub>	007775-09-9	each	O, Xn	1/1	1/0	1/0	1/0	0/0	1/0	2/0	1/1	1/0	0/0	1/3	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/1	2/3	0/0	1/0	1/1L	1/1L	1/1	Chloric acid, sodium salt;	
Sodium chlorate	NaClO <sub>3</sub>	007775-09-9	aqueous	O, Xn	0/0	0/0	3/0	1/0	1/0	0/0	2/0	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/1	3/3	0/0	1/0	1/1L	1/1L	1/1		
Sodium chloride	NaCl	007647-14-5	each	—	1/1	1/1	1/0	1/1	1/1	1/2	1/1	1/1	1/1	1/1	1/3	1/3	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	3/4	1/2	1/2	1/1			
Sodium chloride	NaCl	007647-14-5	aqueous	—	1/1	1/1	1/1	1/1	1/1	1/2	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	3/4	1/2	1/2	1/1	
Sodium chlorite	NaClO <sub>2</sub>	007758-19-2	diluted	(O, Xn)	1/0	1/3	1/4	(2)	0/0	0/0	(2)	1/3	0/0	0/0	3/0	4/4	0/0	(1)	1/1	1/1	1/0	1/1	4/4	0/0	3/4	3/4	3/3	0/0			
Sodium chromate	NaCrO <sub>4</sub>	007775-11-3	diluted	T	1/0	1/0	1/1	(2)	0/0	0/0	(2)	1/1	1/1	0/0	1/3	0/0	1/1	0/0	(1)	1/1	1/1	1/0	1/0	1/3	0/0	1/1	1/1	1/1	0/0		
Sodium cyanide	CNNa	000143-33-9	saturated	T	1/1	1/1	1/0	(3)	0/0	0/0	3/0	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/0	3/3	0/0	4/4	(2)	(2)	0/0	Hydrocyanic acid, sodium salt;	
Sodium cyanide	CNNa	000143-33-9	aqueous	T	1/1	1/1	1/0	(3)	1/0	0/0	3/0	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/0	1/0	0/0	4/4	(2)	(2)	0/0		
Sodium dichromate	Na <sub>2</sub> Cr <sub>2</sub> O <sub>7</sub>	010588-01-9	T	0/0	1/1	1/0	1/0	3/0	1/1	(3)	1/1	1/1	0/0	1/0	0/0	0/0	1/1	(1)	1/1	1/1	1/0	1/0	3/3	0/0	1/1	(1)	(1)	1/1			
Sodium dithionite	-> see: Sodium hydrosulfite																														
Sodium dodecylbenzene sulfonate	C <sub>18</sub> H <sub>35</sub> NaSO <sub>3</sub>	025155-30-0	Xn	1/1	1/1	(2)	(2)	1/0	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	(1)	(1)	(1)	(2)	0/0	(2)	(1)	(1)				
Sodium ferrocyanide	C <sub>6</sub> FeNa <sub>6</sub>	013601-19-9	Xn	1/1	1/1	(1)	(2)	1/0	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	(1)	(1)	(1)	(2)	0/0	(1)	(1)	(1)				
Sodium fluoride	NaF	007681-49-4	saturated	T	1/1	1/1	1/0	(2)	1/0	1/1	1/1	1/0	0/0	1/0	1/3	1/1	0/0	1/1	1/1	1/1	1/0	1/0	1/0	1/0	0/0	1/1	0/0	0/0	0/0	1/1	
Sodium hydrosulfite	Na <sub>2</sub> S <sub>2</sub> O <sub>4</sub>	007775-14-6	10 %	Xn	1/1	0/0	(2)	(2)	(2)	0/0	(2)	1/1	0/0	0/0	1/3	0/0	1/1	0/0	(1)	1/1	1/3	1/0	1/1	3/3	0/0	4/4	1/1	1/1		Sodium dithionite; Dithionous acid, disodium salt; Sodium sulfoxylate;	
Sodium hydrosulfite	Na <sub>2</sub> S <sub>2</sub> O <sub>4</sub>	007775-14-6	aqueous	Xn	1/1	0/0	(2)	(2)	(2)	0/0	(2)	1/1	0/0	0/0	1/3	0/0	1/1	0/0	(1)	1/1	1/3	1/0	1/1	3/3	0/0	4/4	1/1	1/1			
Sodium hydroxide	NaOH	001310-73-2	concentrated	C	1/1	1/1	1/3	4/4	4/4	0/0	(3)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	0/0	1/1	(2)	1/0	4/4	3/4	0/0	4/4	(2)	(2)	?	caustic soda, sodium hydrate, soda lye	
Sodium hydroxide	NaOH	001310-73-2	30 %	C+	1/1	1/1	1/0	4/4	4/4	1/0	1/3	1/1	1/0	1/0	1/3	1/3	0/0	0/0	1/1	(1)	(2)	1/0	(3)	2/3	0/0	4/4	1/3	1/3	1/1	caustic soda, sodium hydrate, soda lye	
Sodium hydroxide	NaOH	001310-73-2	45 %	C+	1/1	1/1	1/0	4/4	4/4	1/0	1/3	1/1	1/1	1/0	1/3	1/3	1/1	0/0	0/0	1/1	(2)	1/0	2/4	2/3	0/0	4/4	1/3	1/3	1/1	caustic soda, sodium hydrate, soda lye	
Sodium hydroxide	NaOH	001310-73-2	50 %	C+	1/1	1/1	1/0	4/4	4/4	1/1	1/3	1/1	2/2	1/1	1/2	0/0	0/3	1/1	1/1	1/1	3/3	1/0	3/4	3/3	0/0	4/4	1/3	1/3	1/1	caustic soda, sodium hydrate, soda lye	
Sodium hydroxide	NaOH	001310-73-2	60 %	C+	1/1	1/1	1/0	4/4	4/4	1/0	(3)	1/1	1/0	0/0	0/0	0/0	0/0	0/0	1/1	(2)	1/0	3/4	2/3	0/0	4/4	1/3	1/3	1/1	1/1	caustic soda, sodium hydrate, soda lye	
Sodium hydroxide	NaOH	001310-73-2	1 %	Xi	1/1	1/1	1/0	3/4	(3)	1/1	1/1	1/1	2/2	1/1	1/1	0/0	0/0	1/1	1/1	1/1	1/0	1/1	1/0	1/1	1/3	0/0	(4)	1/1	1/1	caustic soda, sodium hydrate, soda lye	
Sodium hypochlorite	NaClO	007681-52-9	diluted	(O, C)	2/3	2/3	4/4	(3)	3/0	1/3	4/4	2/3	1/3	1/1	1/3	1/0	1/1	0/0	1/1	1/1	1/1	3/0	1/3	4/4	0/0	4/4	3/3L	2/2L	0/0	sodium oxychloride, sodium chloride oxide	
Sodium hypochlorite	NaClO	007681-52-9	15 %	O, C	2/3	2/3	4/4	2/3	(3)	1/3	4/4	2/3	1/3	1/1	1/1	0/0	1/1	1/1	1/1	1/1	3/4	3/0	1/3	4/4	0/0	4/4	3/3L	2/2L	0/0	sodium oxychloride, sodium chloride oxide	
Sodium hypochlorite	NaClO	007681-52-9	saturated	O, C	2/3	2/3	4/4	2/3	(3)	1/3	4/4	2/3	1/3	1/1	1/3	0/0	1/1	0/0	(1)	1/1	(3)	3/0	1/3	4/4	0/0	4/4	3/3L	2/2L	0/0	sodium oxychloride, sodium chloride oxide	
Sodium hypochlorite	NaClO	007681-52-9																													











## Chemical resistance

Two values are given per substance  
left number = value at +20°C / right number = value at +50°C.

0	no data available	データなし
1	resistant	耐性あり
2	practically resistant	実質的に耐性あり
3	partially resistant	部分的に耐性あり
4	not resistant	耐性なし
K	no general information available	一般情報なし
L	danger of pitting or stress-cracking corrosion	孔食または応力割れ腐食の危険性
( )	estimated value	推定値

## Hazard notes

E	explosive	爆発性
O	oxidizing	酸化性
F	highly flammable	引火性
F+	extremely flammable	引火性
T	toxic	有毒
T+	very toxic	猛毒
C	corrosive	腐食性
Xn	harmful	有害
Xi	irritant	刺激性
N	dangerous for the environment	環境に危険

## Description of the materials

### Thermoplastics

<b>HDPE</b>	Polyethylene (high density)
<b>LDPE</b>	Polyethylene (low density)
<b>PA</b>	Polyamide (Nylon)
<b>PC</b>	Polycarbonate
<b>PETG</b>	Polyethylene terephthalate glycol (PET copolymer)
<b>PMP</b>	Polymethylpentene (TPX)
<b>POM</b>	Polyoxymethylene, polyacetal
<b>PP</b>	Polypropylene
<b>PS</b>	Polystyrene
<b>PSU</b>	Polysulfone
<b>PVC</b>	Polyvinyl chloride
<b>SAN</b>	Styrene-acrylonitrile

### Fluoroplastics

<b>E-CTFE</b>	Ethylene-chlorotrifluoroethylene (Halar )
<b>ETFE</b>	Ethylene-tetrafluoroethylene
<b>FEP</b>	Tetrafluoroethylene-perfluoropropylene (Teflon, FEP)
<b>PTFE</b>	Polytetrafluoroethylene (Teflon)
<b>PVDF</b>	Polyvinylidene fluoride

### Elastomers

<b>EPDM</b>	Ethylene-propylene-diene rubber
<b>FPM/FKM</b>	Fluorinated rubber (Viton)
<b>NBR</b>	Acryl-nitrile-butadiene rubber
<b>SI</b>	Silicone rubber

### Metals

<b>Al</b>	Aluminium
<b>V2A</b>	Stainless steel 1.4301 (AISI 304)
<b>V4A</b>	Stainless steel 1.4401 (AISI 316)
<b>Hastelloy C</b>	Nickel-chromium-molybdenum alloy